

## Technical Data Sheet

### Hostacom PF062-3C NA P23944 BLK



Polypropylene Compounds

#### Product Description

Hostacom PF062-3C NA P23944 BLK high melt flow, 6,600 MPa flexural modulus, precolored, chemically coupled, 30% glass fiber-reinforced polypropylene homopolymer has good impact strength, high stiffness and very good moldfilling capability.

<b>Application</b>	Automotive Parts; Exterior Automotive Applications; Underhood
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding

<b>Typical Properties</b>	<b>Nominal Value</b>	<b>Units</b>	<b>Test Method</b>
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	20	g/10 min	ASTM D1238
Density, (23 °C)	1.12	g/cm <sup>3</sup>	ASTM D792
<b>Mechanical</b>			
Flexural Modulus	6600	MPa	ASTM D790
Tensile Strength at Yield	90	MPa	ASTM D638
<b>Impact</b>			
Notched Izod Impact Strength, (23 °C)	85	J/m	ASTM D256
<b>Additional Information</b>			
Mold Shrinkage			ISO 294-4

Please contact LyondellBasell for shrinkage recommendations.