

## Technical Data Sheet

### Hostacom TRC 103P G71322

Polypropylene Compounds

#### Product Description

Hostacom TRC 103P G71322 is a 16% talc filled PP copolymer, with high flowability, high impact resistance and good stiffness. The product is available in different color matched, pellet form. This grade is delivered in G71322 color version.

#### Regulatory Status

For regulatory compliance information, see Hostacom TRC 103P G71322 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

<b>Status</b>	Commercial: Active
<b>Availability</b>	Europe
<b>Application</b>	Automotive Parts; Interior Trims
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Fast Cycle (Production); Good Dimensional Stability; Good Processability; High Flow; High Impact Resistance; UV Resistant

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	23	g/10 min	ISO 1133-1
Density, (23 °C)	1	g/cm <sup>3</sup>	ISO 1183-1/A
<b>Mechanical</b>			
Flexural Modulus, (23 °C, Tech. A)	1450	MPa	ISO 178/A1
<b>Impact</b>			
Notched Izod Impact Strength			
(23 °C)	20	kJ/m <sup>2</sup>	ISO 180/1A
(-30 °C)	5	kJ/m <sup>2</sup>	ISO 180/1A
<b>Thermal</b>			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	95	°C	ISO 75B-1, -2

#### Notes

These are typical property values not to be construed as specification limits.