

## Technical Data Sheet

### Hostacom TRC 103P G73024



Polypropylene Compounds

#### Product Description

Hostacom TRC 103P G73024 is a 15% talc filled PP copolymer, with high impact resistance. The product is also available as a customized color matched, pellet form. This grade is delivered in G73024 color version

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

<b>Application</b>	Interior Trims
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Fast Cycle (Production); Good Dimensional Stability; Good Processability; Good UV Resistance; High Flow; High Impact Resistance

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	23	g/10 min	ISO 1133-1
Density, (23 °C)	1	g/cm <sup>3</sup>	ISO 1183-1/A
<b>Mechanical</b>			
Flexural Modulus, (23 °C, Tech. A)	1500	MPa	ISO 178/A1
Tensile Strength, (23 °C)	20	MPa	ISO 527-1, -2
<b>Impact</b>			
Notched Izod Impact Strength			
(23 °C)	42	kJ/m <sup>2</sup>	ISO 180/1A
(-30 °C)	5.3	kJ/m <sup>2</sup>	ISO 180/1A
<b>Thermal</b>			
Deflection Temperature Under Load			
(0.45 MPa, Unannealed)	95	°C	ISO 75B-1, -2
(1.80 MPa, Unannealed)	54	°C	ISO 75A-1, -2