

Technical Data Sheet

Hostacom TYS 611N PK79

Polypropylene Compounds

Product Description

Hostacom TYS 611N PK79 is an unfilled impact modified polypropylene, with superior flowability, high scratch resistance offering an excellent impact/stiffness balance. This grade is delivered in PK79 color version.

This product is also available in other colors, new colors can be developed depending on customer requirements.

Regulatory Status

For regulatory compliance information, see Hostacom TYS 611N PK79 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Asia-Pacific
Application	Interior Trims
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Processability; High Flow; High Impact Resistance; Low Density; Scratch Resistant; UV Resistant

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	30	g/10 min	ISO 1133-1
Density, (23 °C, Method A)	0.90	g/cm ³	ISO 1183-1
Mechanical			
Flexural Modulus	1200	MPa	ISO 178
Tensile Stress at Yield	19	MPa	ISO 527-1, -2
Tensile Strain at Break	100	%	ISO 527-1, -2
Impact			
Notched Izod Impact Strength, (23 °C)	45	kJ/m ²	ISO 180/1A
Thermal			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	84	°C	ISO 75B-1, -2

Notes

These are typical property values not to be construed as specification limits.