

Technical Data Sheet  
**Lucent PP CPP-330**  
Polypropylene  
Engineering Plastics



**Product Description**

30% Calcium Carbonate Filled, Impact Modified Polypropylene

Melt Flow Adjustable for Application

Colors Available

Add "U" for UV Stabilized

Add "H" for Heat Stabilized

**General**

Filler / Reinforcement	• Calcium Carbonate, 30% Filler by Weight
Additive	• Impact Modifier
Features	• Impact Modified
Appearance	• Colors Available

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.14	1.14 g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow (0.125 in (3.18 mm))	0.012 in/in	1.2 %	

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	2800 psi	19.3 MPa	ASTM D638
Tensile Elongation (Break)	> 10 %	> 10 %	ASTM D638
Flexural Modulus	250000 psi	1720 MPa	ASTM D790
Flexural Strength	5300 psi	36.5 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (0.125 in (3.18 mm))	2.8 ft·lb/in	150 J/m	ASTM D256

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 264 psi (1.8 MPa), Unannealed	145 °F	62.8 °C	ASTM D648

**Notes**

These are typical property values not to be construed as specification limits.