

Technical Data Sheet

Pro-fax EP545U

Polypropylene, Impact Copolymer

Product Description

Pro-fax EP545U high flow polypropylene impact copolymer is available in pellet form. This resin is typically used in thin-wall injection molding applications and offers very good stiffness/impact balance.

Regulatory Status

For regulatory compliance information, see *Pro-fax* EP545U [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	North America
Application	TWIM Food Containers
Market	Rigid Packaging
Processing Method	Injection Molding
Attribute	Contains Antistat; Good Stiffness; High Flow; Medium Slip; Nucleated

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (230 °C/2.16 kg)	80	g/10 min	80	g/10 min	ASTM D1238
Density, (23 °C)	0.90	g/cm ³	0.90	g/cm ³	ASTM D792
Mechanical					
Flexural Modulus					
(0.05 in/min, 1% Secant, Procedure A)	180000	psi			ASTM D790
(1.3 mm/min, 1% Secant, Procedure A)			1240	MPa	ASTM D790
Tensile Strength at Yield					
(2 in/min)	3500	psi			ASTM D638
(50 mm/min)			24	MPa	ASTM D638
Tensile Elongation at Yield	4	%	4	%	ASTM D638
Impact					
Notched Izod Impact Strength					
(73 °F, Method A)	1.7	ft-lb/in			ASTM D256
(23 °C, Method A)			91	J/m	ASTM D256
Thermal					
Deflection Temperature Under Load					
(66 psi, Unannealed)	226	°F			ASTM D648
(0.45 MPa, Unannealed)			108	°C	ASTM D648

Notes

These are typical property values not to be construed as specification limits.