

CELSTRAN® PA6-GF30-01 | PA6 | Glass Reinforced

Description


30% long strand glass fiber reinforced nylon 6 Black

Physical properties	Value	Unit	Test Standard
Specific gravity	1.36	-	ASTM D792
Mold shrinkage - flow direction	.0005-.001	in/in	ASTM D955
Mold shrinkage - transverse direction	.003-.004	in/in	ASTM D955

Mechanical properties	Value	Unit	Test Standard
Elongation @ break (250°F)	3	%	ASTM D638
Elongation @ break (-40°F)	3.1	%	ASTM D638
Elongation @ break (73°F)	2.6	%	ASTM D638
Tensile modulus (-40°F)	1.40E6	psi	ASTM D638
Tensile modulus (73°F)	1.50E6	psi	ASTM D638
Tensile modulus (250°F)	8.40E5	psi	ASTM D638
Tensile strength @ break (-40°F)	33500	psi	ASTM D638
Tensile strength @ break (73°F)	29500	psi	ASTM D638
Tensile strength @ break (250°F)	12700	psi	ASTM D638

Thermal properties	Value	Unit	Test Standard
Heat deflection temperature @264 psi	405	°F	ASTM D648

Typical injection moulding processing conditions



Pre Drying:

Necessary low maximum residual moisture content: 0.18%

CELSTRAN PA should in principle be predried. Because of the necessary low maximum residual moisture content the use of dry air dryers is recommended. The dew point should be $\leq -30^{\circ}\text{C}$. The time between drying and processing should be as short as possible.

Note: Material can be over dried and may discolor.

Drying time: 2 - 4 h

Drying temperature: 158 - 176 °F

CELSTRAN® PA6-GF30-01 | PA6 | Glass Reinforced

Temperature:

	°Mold	°Melt	°Nozzle	°Zone4	°Zone3	°Zone2	°Zone1	°Feed	°Hopper
min (°F)	176	518	518	518	518	509	500	68	158
max (°F)	212	536	536	536	536	527	518	122	176

Injection Molding

Celstran can be processed on a standard injection molding unit. A general purpose metering screw is recommended with a zone distribution of 40% feed, 40% transition, and 20% metering. A free flowing check ring assembly is recommended.

Melt Temp: 270-280°C.

Mold Temp: 85- 95°C.

Contact Information

Americas

8040 Dixie Highway, Florence, KY 41042 USA

Product Information Service

t: +1-800-833-4882 t: +1-859-372-3244

Customer Service

t: +1-800-526-4960 t: +1-859-372-3214

e: info-engineeredmaterials-am@celanese.com

Asia

4560 Jinke Road, Zhang Jiang Hi Tech Park

Shanghai 201203 PRC

Customer Service

t: +86 21 3861 9266 f: +86 21 3861 9599

e: info-engineeredmaterials-asia@celanese.com

Europa

Am Unisys-Park 1, 65843 Sulzbach, Germany

Product Information Service

t: +(00)-800-86427-531 t: +49-(0)-69-45009-1011

e: info-engineeredmaterials-eu@celanese.com

General Disclaimer

This publication was printed based on Celanese's present state of knowledge, and Celanese undertakes no obligation to update it. Because conditions of product use are outside Celanese's control, Celanese makes no warranties, express or implied, and assumes no liability in connection with any use of this information. Nothing herein is intended as a license to operate under or a recommendation to infringe any patents.

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colorants or other additives may cause significant variations in data values.

Properties of molded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use.

To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication.

Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards.

We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed (+49 (0) 69 30516299 for Europe, +1 859-372-3244 for the Americas and +86 21 3861 9266 for Asia) for additional technical information. Visit our web site for the appropriate Safety Data Sheets (SDS) before attempting to process our products. Feel free to call Customer Services for additional assistance.

The products mentioned herein are not intended for use in medical or dental implants.

© 2014 Celanese or its affiliates. All rights reserved. (Published 21.Dec.2015)

Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC.