

TECHNICAL DATA SHEET

TECHNYL PROTECT C 60 MX10 V10 GY 7513
(Previously DOMAMID FR 6GT2010V0E)

Polyamide 6, 20% glass fiber and mineral filler, heat-aging stabilized, halogen and red phosphorus free flame retardant, for injection moulding

General

Feature	UL V0 Heat-aging stabilized	Halogen and red phosphorus free flame retardant
Polymer type	PA6 (Polyamide 6)	
Processing technology	Injection molding	
Certification	RoHS	

Product identification

ISO 1043 abbreviation	PA6-(GF10+MD10) FR(40)
ISO 16396 designation	PA6,(GF+MD)20FR(40),M1H,S14-080

	Condition	Standard	Unit	Value
Density		ISO 1183	g/cm³	1.37

Physical properties

				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	7900 / -
Stress at break	5 mm/min	ISO 527-1/-2	MPa	85 / -
Strain at break	5 mm/min	ISO 527-1/-2	%	3 / -
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	6500 / -
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	120 / -
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m²	35 / -
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m²	4.5 / -
Izod impact strength, +23°C	+23°C	ISO 180/1U	kJ/m²	30 / -
Izod notched impact strength, +23°C	+23°C	ISO 180/1A	kJ/m²	4.5 / -

Thermal properties

Melting temperature, 10°C/min		ISO 11357-1	°C	221
-------------------------------	--	-------------	----	-----

TECHNICAL DATA SHEET

TECHNYL PROTECT C 60 MX10 V10 GY 7513

	Condition	Standard	Unit	Value
Electrical properties				
Volume resistivity		IEC 62631-3-1	ohm.m	1E+013
Surface resistivity		IEC 62631-3-1	ohm	1E+013
Comparative tracking index	Solution A	IEC 60112	V	575
CTI performance level category		Sol A		PLC 1

Burning behaviour

Flammability, 0.75 mm	0.75 mm	UL 94		V0
Flammability, 1.5 mm	1.5 mm	UL 94		V0
Flammability, 3.0 mm	3.0 mm	UL 94		V0
Glow-wire flammability index, GWFI	1-3 mm	IEC 60695-2-12	°C	960
Glow-wire ignition temperature, GWIT	1-3 mm	IEC 60695-2-13	°C	750
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		< 100 mm/min

Test run at 23°C if not differently specified, DAM state (dry as moulded), valid for natural colored products.
*: conditioned according to ISO 1110

Processing conditions

Drying temperature/time	75-85°C / 2-4h (with dew point of dried air < -30 °C)
Recommended melt temperature	240 - 260 °C
Recommended mould temperature	70 - 90 °C

These parameters are typical of the product but should be related to the type of machinery used and to the type of moulded part.

Disclaimer

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Domo cannot anticipate all conditions under which this information and our products of other manufactures in combination with our products may be used. Domo accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Domo sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.