Component - Plastics

File Number: E56070

CHI MEI CORPORATION
59-1 SAN CHIA
JEN TE
TAINAN, 717 Taiwan

WONDERLOY: PC-540(Y)(a)

Polycarbonate/Acrylonitrile Butadiene Styrene (PC/ABS), pellets

(a) - Ball pressure temperature is in accordance with IEC 60695-10-2 Method B.
(Y) - Optional suffix; may be suffixed with one or two alphabet but except H, unconcerned with formula or constituent changed.

Flammability	Value	Test Method
Flame Rating		
0.75 mm, ALL	HB	UL 94
0.8 mm, ALL	V-2	UL 94 IEC 60695-11-10, -20
1.5 mm, ALL	V-0	UL 94 IEC 60695-11-10, -20
2.0 mm, ALL	V-0, 5VB	UL 94 IEC 60695-11-10, -20
2.5 mm, ALL	V-0, 5VA	UL 94 IEC 60695-11-10, -20
3.0 mm, ALL	V-0, 5VA	UL 94 IEC 60695-11-10, -20
0.75 mm, ALL	HB75	IEC 60695-11-10, -20
Glow Wire Flammability Index		IEC 60695-2-12
1.5 mm	960 °C	
3.0 mm	960 °C	
Glow Wire Ignition Temperature		IEC 60695-2-13
1.5 mm	800 °C	
3.0 mm	750 °C	
Electrical	**Value**	**Test Method**
Hot-wire Ignition (HWI)		UL 746A
0.75 mm	PLC 3	
0.8 mm	PLC 3	
1.5 mm	PLC 3	
2.0 mm	PLC 3	
2.5 mm	PLC 3	
3.0 mm	PLC 3	
High Amp Arc Ignition (HAI)		UL 746A
0.75 mm	PLC 3	
0.8 mm	PLC 3	
1.5 mm	PLC 3	
2.0 mm	PLC 3	
2.5 mm	PLC 3	
3.0 mm	PLC 2	
Comparative Tracking Index (CTI)	PLC 2	UL 746A
Dielectric Strength	32 kV/mm	ASTM D149
High Voltage Arc Tracking Rate (HVTR)	PLC 3	UL 746A
Volume Resistivity	1.0E+14 ohms·cm	ASTM D257 IEC 60093

Form Number: E56070-100269744

UL and the UL logo are trademarks of UL LLC Copyright © 2021 All Rights Reserved. | www.ul.com

Report Date: 1/12/2001
Last Revised: 6/9/2020 10:05:14 PM

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

塑料专家 www.ponci.com.cn/wxb/ +13538586433 +18816996168

Component - Plastics

File Number: E56070

Electrical	Value	Test Method
Arc Resistance	PLC 5	ASTM D495
Thermal	**Value**	**Test Method**
RTI Elec		UL 746B
0.75 mm	60.0 °C	
0.8 mm	60.0 °C	
1.5 mm	85.0 °C	
2.0 mm	85.0 °C	
2.5 mm	85.0 °C	
3.0 mm	85.0 °C	
RTI Imp		UL 746B
0.75 mm	60.0 °C	
0.8 mm	60.0 °C	
1.5 mm	80.0 °C	
2.0 mm	80.0 °C	
2.5 mm	80.0 °C	
3.0 mm	80.0 °C	
RTI Str		UL 746B
0.75 mm	60.0 °C	
0.8 mm	60.0 °C	
1.5 mm	80.0 °C	
2.0 mm	80.0 °C	
2.5 mm	80.0 °C	
3.0 mm	80.0 °C	
Ball Pressure Test (90°C)	Pass	IEC 60695-10-2
Physical	**Value**	**Test Method**
Dimensional Change	0.0 %	ASTM D1042 ISO 2796

Form Number: E56070-100269744

UL and the UL logo are trademarks of UL LLC Copyright © 2021 All Rights Reserved. | www.ul.com

Report Date: 1/12/2001
Last Revised: 6/9/2020 10:05:14 PM

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

塑料专家 www.ponci.com.cn/wxb/ +13538586433 +18816996168