



AMPLIFY™ EA 100

The Dow Chemical Company - Functional Polymer

Sunday, November 3, 2019

General Information

Product Description

AMPLIFY™ EA 100 Functional Polymer is produced via a high-pressure reactor. This ethylene-ethyl acrylate (EEA) copolymer exhibits high flexibility and imparts low temperature toughness to a wide range of engineering resins. This polymer demonstrates excellent blend compatibility with other polyolefins. It can be utilized as a tie layer between polyolefins and a variety of polar substrates, such as metal, polyvinylidene chloride (PVDC), polyolefins, cellulose, polyester, polycarbonate, glass, foil, PVC, PET, and Polystyrene.

- High performance packaging applications
- Polymer modification
- Tie layer to PVDC and Polyolefins
- Extrusion grade for profile and tubing
- Superior additive concentrate carrier
- Excellent thermal stability

Complies with:

- U.S. FDA 21 CFR 175.105
- U.S. FDA 21 CFR 177.1320 (with Restrictions)
- EU, No 10/2011

Consult the regulations for complete details.

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific • Europe	• Latin America • North America	
Additive	• Antiblock: No	• Processing Aid: No	• Slip: No
Agency Ratings	• EU No 10/2011	• FDA 21 CFR 175.105	• FDA 21 CFR 177.1320
Forms	• Pellets		
Processing Method	• Blow Molding	• Extrusion Coating	• Injection Molding

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.932		ASTM D792
Density	0.930	g/cm ³	ISO 1183
Melt Mass-Flow Rate (190°C/2.16 kg)	1.3	g/10 min	ASTM D1238
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.3	g/10 min	ISO 1133
Comonomer Content ²	15.0	%	ASTM D3594
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	550	psi	ASTM D638
Tensile Stress (Yield)	550	psi	ISO 527-2
Tensile Strength (Break)	2600	psi	ASTM D638
Tensile Stress (Break)	2600	psi	ISO 527-2
Tensile Elongation (Yield)	8.0	%	ASTM D638
Tensile Strain (Yield)	8.0	%	ISO 527-2
Tensile Elongation (Break)	750	%	ASTM D638
Tensile Strain (Break)	750	%	ISO 527-2
Flexural Modulus - 2% Secant	9700	psi	ASTM D790B
Flexural Modulus - 2% Secant	9700	psi	ISO 178

AMPLIFY™ EA 100

The Dow Chemical Company - Functional Polymer

Impact	Nominal Value	Unit	Test Method
Tensile Impact Strength ³	No Break		ASTM D1822
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A	87		
Shore D	37		
Shore Hardness			ISO 868
Shore A	87		
Shore D	37		
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	91.0	°F	ASTM D648
Brittleness Temperature	< -105	°F	ASTM D746
Vicat Softening Temperature	153	°F	ASTM D1525
Vicat Softening Temperature	153	°F	ISO 306
Melting Temperature (DSC)	210	°F	Internal Method
Peak Crystallization Temperature (DSC)	180	°F	Internal Method

Additional Information

Molded and tested in accordance with ASTM D4976.

Notes

¹ Typical properties: these are not to be construed as specifications.

² Calibration Range is 15 - 20% EA; Pathlength is normalized; Plaque/Film Thickness is 15 mil; Press Temperature is 160°C

³ Type S