



AMPLIFY™ TY 1052H

The Dow Chemical Company - Functional Polymer

Sunday, November 3, 2019

General Information

Product Description

AMPLIFY™ TY 1052H Functional Polymer is a maleic anhydride grafted (MAH) polymer concentrate designed as a blend component for unmodified polyethylene and polypropylene. In tie layers for flexible packaging, AMPLIFY TY 1052H Functional Polymer promotes adhesion of polyethylene and polypropylene to barrier polymers such as polyamide and ethylene vinyl alcohol (EVOH). The functionality of this polymer also promotes adhesion between metal, polyolefins, cellulose, polyester, polycarbonate, glass, and foil.

Typical blending levels in polyethylene let-down resin are 20-25% for EVOH and 10-15% for nylon.

Main Characteristics:

- Adhesive concentrate for use in blown, cast, and coating applications
- Tie layer for food packaging and pipe coating
- Adhesive layer in multi-layer flexible film applications
- Polymer compatibilizer

Complies with:

- U.S. FDA 21 CFR 175.105
- EU, No 10/2011

Consult the regulations for complete details.

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific • Europe	• Latin America • North America	
Additive	• Antiblock: No	• Processing Aid: No	• Slip: No
Agency Ratings	• EU No 10/2011	• FDA 21 CFR 175.105	
Forms	• Pellets		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	0.875	g/cm ³	ASTM D792
Melt Mass-Flow Rate (190°C/2.16 kg)	1.3	g/10 min	ASTM D1238
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.3	g/10 min	ISO 1133
MAH Graft Level ²	High		Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	1300	psi	ASTM D638
Tensile Stress (Break)	1300	psi	ISO 527-2/51
Tensile Elongation (Break)	1000	%	ASTM D638
Tensile Strain (Break)	1000	%	ISO 527-2/51
Flexural Modulus - 2% Secant	2000	psi	ASTM D790A
Flexural Modulus - 2% Secant	2000	psi	ISO 178
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A	77		
Shore D	21		

AMPLIFY™ TY 1052H

The Dow Chemical Company - Functional Polymer

Hardness	Nominal Value	Unit	Test Method
Shore Hardness			ISO 868
Shore A	77		
Shore D	21		
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	104	°F	ASTM D1525
Vicat Softening Temperature	104	°F	ISO 306
Melting Temperature (DSC)	145	°F	Internal Method

Additional Information

Molded in accordance with ASTM D4976.

Notes

¹ Typical properties: these are not to be construed as specifications.

² Low: <0.25 wt%, Medium 0.25-0.5, High >0.5 wt%, Very High >1.0 wt%.