

Appeel® 20D867

DuPont Packaging & Industrial Polymers - Ethylene Acrylate Copolymer

Sunday, November 3, 2019

General Information

Product Description

DuPont™ Appeel 20D867 is a modified ethylene acrylate resin designed to function as a sealing layer for lidding applications. It is most often suggested to provide peelable seals over a broad temperature range to a number of container materials including PET, PVC, PS and PP. Appeel 20D867 is available in pellet form for use in conventional extrusion and coextrusion equipment designed to process polyethylene resins.

General					
Material Status	Experimental: Active				
Availability	 Africa & Middle East Asia Pacific	EuropeLatin America	North America		
Uses	• Lids	Seals			
Agency Ratings	• FDA 21 CFR 177.1340				
Forms	• Pellets				
Processing Method	Coextrusion	Extrusion			

ASTM & ISO Properties 1					
Physical	Nominal Value	Unit	Test Method		
Density / Specific Gravity	0.943		ASTM D792		
Density	0.941	g/cm³	ISO 1183		
Melt Mass-Flow Rate (190°C/2.16 kg)	9.0	g/10 min	ASTM D1238		
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	9.0	g/10 min	ISO 1133		
Thermal	Nominal Value	Unit	Test Method		
Vicat Softening Temperature	117	°F	ASTM D1525		
Vicat Softening Temperature	117	°F	ISO 306		
Peak Melting Temperature	194	°F	ASTM D3418		
Melting Temperature (DSC)	194	°F	ISO 3146		
Wolling Temperature (BOO)	104	•	100 0140		

Processing Information				
Extrusion	Nominal Value Unit			
Cylinder Zone 1 Temp.	284 °F			
Cylinder Zone 2 Temp.	302 °F			
Cylinder Zone 3 Temp.	320 °F			
Cylinder Zone 4 Temp.	356 °F			
Cylinder Zone 5 Temp.	356 °F			
Adapter Temperature	356 °F			
Melt Temperature	320 to 365 °F			
Die Temperature	338 °F			



Appeel® 20D867

DuPont Packaging & Industrial Polymers - Ethylene Acrylate Copolymer

Extrusion Notes

The above processing values are for blown film.

Extrusion coating/lamination parameters:

Feed Zone: 160°C
Second Zone: 210°C
Third Zone: 260°C
Fourth Zone: 285°C
Fifth Zone: 285°C
Adapter Zone: 285°C
Die Zone: 285°C

• Melt Temperature: 235 to 285°C

Notes

¹ Typical properties: these are not to be construed as specifications.

