

# Appeel® 72D799

## DuPont Packaging & Industrial Polymers - Ionomer

Sunday, November 3, 2019

#### **General Information**

#### **Product Description**

DuPont™ Appeel® 72D799 is a blown or cast film resin designed to be a sealing layer to film or sheet lidding applications. It provides a peelable seal to a number of materials including HDPE, LLDPE, LDPE, EVA, and Ionomer.

Appeel® 72D799 is a modified ionomer polymer available in pellet form for use in conventional extrusion and coextrusion equipment designed to process polyethylene resins.

General					
Material Status	Experimental: Active				
Availability	<ul><li>Africa &amp; Middle East</li><li>Asia Pacific</li></ul>	<ul><li>Europe</li><li>Latin America</li></ul>	North America		
Features	Food Contact Acceptable				
Uses	• Lids	<ul> <li>Sealants</li> </ul>			
Agency Ratings	• FDA 21 CFR 177.1330				
Forms	<ul> <li>Pellets</li> </ul>				
Processing Method	Coextrusion	Extrusion			

ASTM & ISO Properties <sup>1</sup>					
Physical	Nominal Value	Unit	Test Method		
Density / Specific Gravity	0.934		ASTM D792		
Density	0.932	g/cm³	ISO 1183		
Melt Mass-Flow Rate (190°C/2.16 kg)	2.9	g/10 min	ASTM D1238		
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.9	g/10 min	ISO 1133		
Thermal	Nominal Value	Unit	Test Method		
Peak Melting Temperature	201	°F	ASTM D3418		
Melting Temperature (DSC)	201	°F	ISO 3146		

Processing Information			
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	275	°F	
Cylinder Zone 2 Temp.	320	°F	
Cylinder Zone 3 Temp.	365	°F	
Cylinder Zone 4 Temp.	365	°F	
Cylinder Zone 5 Temp.	365	°F	
Adapter Temperature	365	°F	
Melt Temperature	320 to 365	°F	
Die Temperature	347	°F	

### Notes



<sup>&</sup>lt;sup>1</sup> Typical properties: these are not to be construed as specifications.