

## Ateva® 1941

## Celanese EVA Performance Polymers - Ethylene Vinyl Acetate Copolymer

Sunday, November 3, 2019

General Information				
Product Description				
This resin is commonly used for	r extrusion coating, coextrusion and specia	alty lamination applications.		
General				
Material Status	Commercial: Active			
Availability	• Europe	North America		
Additive	<ul> <li>Medium Antiblock</li> </ul>	Medium Slip		
Features	<ul> <li>Copolymer</li> </ul>			
Uses	<ul> <li>Coating Applications</li> </ul>	<ul> <li>Laminates</li> </ul>		
Agency Ratings	• EC 1907/2006 (REACH)			
Forms	• Pellets			
Processing Method	<ul><li>Coating</li><li>Coextrusion</li></ul>	<ul><li>Compounding Extrusion</li><li>Extrusion</li></ul>	• Laminating	

ASTM & ISO Properties <sup>1</sup>				
Physical	Nominal Value	Unit	Test Method	
Density	0.937	g/cm³	ASTM D1505	
Melt Mass-Flow Rate (190°C/2.16 kg)	30	g/10 min	ASTM D1238	
Vinyl Acetate Content	19.0	wt%		
Films	Nominal Value	Unit	Test Method	
Tensile Strength - MD <sup>2</sup> (Break)	2180	psi	ASTM D882A	
Tensile Strength - TD <sup>2</sup> (Break)	1890	psi	ASTM D882A	
Tensile Elongation - MD <sup>2</sup> (Break)	520	%	ASTM D882A	
Tensile Elongation - TD <sup>2</sup> (Break)	610	%	ASTM D882A	
Thermal	Nominal Value	Unit	Test Method	
Vicat Softening Temperature	124	°F	ASTM D1525	
Peak Melting Temperature	183	°F	ASTM D3418	

Processing Information		
Extrusion	Nominal Value Unit	
Melt Temperature	<410 °F	

## **Notes**



<sup>&</sup>lt;sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>&</sup>lt;sup>2</sup> 20 in/min