



Ateva® 2850A

Celanese EVA Performance Polymers - Ethylene Vinyl Acetate Copolymer

Sunday, November 3, 2019

General Information

Product Description

This resin is commonly used for hot melt coating and adhesive applications.

General

Material Status	• Commercial: Active
Availability	• Europe • North America
Additive	• Antioxidant
Features	• Antioxidant • Copolymer
Uses	• Adhesives • Coating Applications
Agency Ratings	• EC 1907/2006 (REACH)
Forms	• Pellets
Processing Method	• Extrusion Coating

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	0.940	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (125°C/0.325 kg)	850	g/10 min	ASTM D1238
Vinyl Acetate Content	28.0	wt%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (Break)	290	psi	ASTM D638
Tensile Elongation ² (Break)	350	%	ASTM D638
Flexural Modulus - 1% Secant	1600	psi	ASTM D790
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A	64		
Shore D	12		
Thermal	Nominal Value	Unit	Test Method
Ring and Ball Softening Point	174	°F	ASTM E28

Processing Information

Extrusion	Nominal Value	Unit
Melt Temperature	< 410	°F

Notes

¹ Typical properties: these are not to be construed as specifications.

² Type IV, 2.0 in/min