

# Bynel® 4140

DuPont Packaging & Industrial Polymers - Linear Low Density Polyethylene

#### Tuesday, November 5, 2019

#### **General Information**

#### **Product Description**

BYNEL® Series 4100 resins are anhydride-modified, linear low-density polyethylene (LLDPE) resins. All 4100 series resins are available in pellet form for use in conventional extrusion and coextrusion equipment designed to process polyethylene (PE) resin.

BYNEL 4140 is a grade with a higher level of anhydride modification, and is mainly intended for use as a component in a blend with other polyolefin resins. It is not intended for extrusion in its pure form in typical extrusions or coextrusions.

BYNEL 4100 series resins adhere to a variety of materials. They are most often used to adhere to EVOH, polyamide, PE and ethylene copolymers. Series 4100 resins can be used in coextrusion processes including:

- blown film
- · cast film/sheet
- · blow molding
- · melt and solid phase thermoforming
- · sheet and tubing

LLDPE resins are known for their temperature resistance, clarity and toughness.

These physical properties make the 4100 series resins work well in applications such as:

- · boil-in-bag structures
- · blow molded containers in which drop strength is important
- · bag-in-box films
- · film where LLDPE is the heat seal layer.

General			
Material Status	Commercial: Active		
Availability	<ul><li> Africa &amp; Middle East</li><li> Asia Pacific</li></ul>	<ul><li>Europe</li><li>Latin America</li></ul>	North America
Features	Good Adhesion		
Uses	<ul><li>Adhesives</li><li>Blending</li><li>Blow Molding Applications</li></ul>	<ul><li>Cast Film</li><li>Containers</li><li>Film</li></ul>	<ul><li>Sheet</li><li>Tubing</li></ul>
Agency Ratings	• FDA 21 CFR 175.105		
Forms	<ul> <li>Pellets</li> </ul>		
Processing Method	<ul><li>Blow Molding</li><li>Coextrusion</li></ul>	<ul><li>Extrusion</li><li>Solid Phase Press. Form. Thermoforming</li></ul>	Thermoforming

ASTM & ISO Properties <sup>1</sup>					
Physical	Nominal Value		Test Method		
Density / Specific Gravity	0.922		ASTM D792		
Density	0.920	g/cm³	ISO 1183		
Melt Mass-Flow Rate (190°C/2.16 kg)	1.8	g/10 min	ASTM D1238		
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.8	g/10 min	ISO 1133		
Thermal	Nominal Value	Unit	Test Method		
Vicat Softening Temperature	216	°F	ASTM D1525		
Vicat Softening Temperature	216	°F	ISO 306		
Peak Melting Temperature	250	°F	ASTM D3418		
Melting Temperature (DSC)	250	°F	ISO 3146		

our control, and we cannot and will not take responsibility for the information or content



## Bynel® 4140

### DuPont Packaging & Industrial Polymers - Linear Low Density Polyethylene

Thermal	Nominal Value	Unit	Test Method
Freezing Point			
	212	°F	ASTM D3418
	212	°F	ISO 3146
	Processing Information		
Extrusion	Nominal Value	Unit	
Melt Temperature	< 500	°F	

#### **Notes**

<sup>&</sup>lt;sup>1</sup> Typical properties: these are not to be construed as specifications.