



CALIBRE™ MEGARAD™ 2081-6LR

Trinseo - Polycarbonate Resin

Tuesday, November 5, 2019

General Information

Product Description

CALIBRE™ MEGARAD™ 2081-6LR Polycarbonate resin was developed for medical applications requiring improved resistance to lipids over standard polycarbonate resins. When exposed to a 20% intralipid emulsion solution under strained conditions, CALIBRE MEGARAD 2081-6LR exhibits significant property retention compared to standard polycarbonate. It also provides end-users of radiation sterilized medical devices a color closer to the water-clear look of the natural resin. When exposed to high energy radiation (gamma or electron beam), CALIBRE MEGARAD 2081-6LR can reduce the color shift by 50% compared to general purpose polycarbonate resins.

CALIBRE MEGARAD 2081-6LR has been evaluated with respect to ISO 10993 (Biological Evaluation of Medical Devices) and is suitable for use in approved medical applications.

Main Characteristics

- Improved lipid resistance
- Stabilized for high-energy radiation
- Transparent
- Contains mold release
- Tested under ISO 10993

Applications

- Medical applications

General

Material Status	• Commercial: Active
Availability	• Asia Pacific • North America
Additive	• Mold Release
Uses	• Electrical/Electronic Applications • General Purpose • Medical/Healthcare Applications
Agency Ratings	• ISO 10993 ¹
Appearance	• Clear/Transparent
Forms	• Pellets
Processing Method	• Injection Molding

ASTM & ISO Properties ²

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.20		ASTM D792
Melt Mass-Flow Rate (300°C/1.2 kg)	6.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	5.0E-3 to 7.0E-3	in/in	ASTM D955
Water Absorption (24 hr, 73°F)	0.15	%	ASTM D570
Water Absorption (Equilibrium, 73°F, 50% RH)	0.32	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ³	340000	psi	ASTM D638
Tensile Strength ⁴ (Yield)	9500	psi	ASTM D638
Tensile Strength ⁴ (Break)	9900	psi	ASTM D638
Tensile Elongation ⁴ (Yield)	6.0	%	ASTM D638
Tensile Elongation ⁴ (Break)	130	%	ASTM D638
Flexural Modulus ⁵	350000	psi	ASTM D790
Flexural Strength ⁵	14000	psi	ASTM D790

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

CALIBRE™ MEGARAD™ 2081-6LR

Trinseo - Polycarbonate Resin

Mechanical	Nominal Value	Unit	Test Method
Taber Abrasion Resistance	45	%	ASTM D1044
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	16	ft-lb/in	ASTM D256
Unnotched Izod Impact (73°F)	No Break		ASTM D256
Instrumented Dart Impact ⁶ (73°F, Total Energy)	790	in-lb	ASTM D3763
Tensile Impact Strength	270	ft-lb/in ²	ASTM D1822
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	118		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Annealed)	293	°F	ASTM D648
Deflection Temperature Under Load 264 psi, Unannealed	265	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Annealed)	288	°F	ASTM D648
Vicat Softening Temperature	304	°F	ASTM D1525 ⁷
CLTE - Flow	3.8E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	2.0E+17	ohms·cm	ASTM D257
Dielectric Strength	420	V/mil	ASTM D149
Dielectric Constant			ASTM D150
60 Hz	3.00		
1 MHz	3.00		
Dissipation Factor			ASTM D150
50 Hz	1.0E-3		
1 MHz	2.0E-3		
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.586		ASTM D542
Transmittance	85.0	%	ASTM D1003
Haze	1.00	%	ASTM D1003

Notes

¹ Biocompatibility testing following ISO Guidelines 10993 has been completed on select classic resins in this series. Please consult Styron for details. ISO guidelines include a sensitization test.

² Typical properties: these are not to be construed as specifications.

³ 0.039 in/min

⁴ 2.0 in/min

⁵ Method I (3 point load), 0.079 in/min

⁶ 11.1 ft/sec

⁷ Rate A (50°C/h), Loading 2 (50 N)