



Celanex® 5200-2

Celanese Corporation - Polybutylene Terephthalate

Monday, November 4, 2019

General Information

Product Description

Celanex 5200-2 is a 15% fiberglass reinforced polyester with improved surface finish. Celanex 5200-2 contains an internal lubricant.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass Fiber, 15% Filler by Weight		
Additive	• Lubricant		
Features	• Good Surface Finish	• Lubricated	
RoHS Compliance	• Contact Manufacturer		
Automotive Specifications	• CHRYSLER MS-DB-400 CPN2425 Color: Black		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.41	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (265°C/2.16 kg)	28	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (265°C/2.16 kg)	38	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow	0.40 to 0.60	%	ISO 294-4
Water Absorption (Saturation, 73°F)	0.45	%	ISO 62
Water Absorption (Equilibrium, 73°F, 50% RH)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	870000	psi	ISO 527-2/1A
Tensile Stress (Break)	17400	psi	ISO 527-2/1A/5
Tensile Strain (Break)	3.0	%	ISO 527-2/1A/5
Flexural Modulus (73°F)	1.16E+6	psi	ISO 178
Flexural Stress (73°F)	26800	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F	3.8	ft·lb/in ²	
73°F	3.8	ft·lb/in ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F	17	ft·lb/in ²	
73°F	17	ft·lb/in ²	
Notched Izod Impact Strength (73°F)	3.4	ft·lb/in ²	ISO 180/1A
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	91		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (66 psi, Unannealed)	419	°F	ISO 75-2/B
Heat Deflection Temperature (264 psi, Unannealed)	374	°F	ISO 75-2/A
Heat Deflection Temperature (1160 psi, Unannealed)	149	°F	ISO 75-2/C
Vicat Softening Temperature	410	°F	ISO 306/B50
Melting Temperature ²	437	°F	ISO 11357-3
CLTE - Flow	1.9E-5	in/in/°F	ISO 11359-2

Celanex® 5200-2

Celanese Corporation - Polybutylene Terephthalate

Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Electric Strength	710	V/mil	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	4.30		
1 MHz	4.00		
Dissipation Factor			IEC 60250
100 Hz	1.1E-3		
1 MHz	0.019		
Comparative Tracking Index	325	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.030 in)	HB		UL 94
Oxygen Index	20	%	ISO 4589-2

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	248 to 266	°F
Drying Time	4.0	hr
Suggested Max Moisture	0.020	%
Hopper Temperature	68 to 122	°F
Rear Temperature	446 to 482	°F
Middle Temperature	455 to 491	°F
Front Temperature	455 to 491	°F
Nozzle Temperature	482 to 509	°F
Processing (Melt) Temp	455 to 509	°F
Mold Temperature	149 to 199	°F
Injection Rate	Moderate-Fast	

Injection Notes

Die Temperature: 250 to 265°C
Feed Temperature: 230 to 250°C
Zone 4 Temperature: 240 to 260°C

Notes

¹ Typical properties: these are not to be construed as specifications.

² 10°C/min