



Celanex® 5202

Celanese Corporation - Polybutylene Terephthalate

Monday, November 4, 2019

General Information

Product Description

Celanex 5202 is a 15% glass filled polyester that features improved surface gloss and has an excellent balance of mechanical properties, processability, and color stability under heat and UV exposure. A typical application for Celanex 5202 is oven handles.

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • Asia Pacific • Latin America • North America
Filler / Reinforcement	• Glass Fiber, 15% Filler by Weight
Features	• Good Color Stability • Good Gloss • Good Processability
Uses	• Handles
RoHS Compliance	• Contact Manufacturer

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.44	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (265°C/2.16 kg)	25	g/10 min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	0.70	%	
Flow	0.10 to 0.60	%	
Water Absorption (Equilibrium, 73°F, 50% RH)	0.17	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	885000	psi	ISO 527-2/1A
Tensile Stress (Break)	14500	psi	ISO 527-2/1A/5
Tensile Strain (Break)	2.5	%	ISO 527-2/1A/5
Flexural Modulus (73°F)	769000	psi	ISO 178
Flexural Stress (73°F)	21800	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F	2.1	ft-lb/in ²	
73°F	2.2	ft-lb/in ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F	8.1	ft-lb/in ²	
73°F	7.1	ft-lb/in ²	
Notched Izod Impact Strength (73°F)	2.1	ft-lb/in ²	ISO 180/1A
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, 15 sec)	83		ISO 868
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (66 psi, Unannealed)	419	°F	ISO 75-2/B
Heat Deflection Temperature (264 psi, Unannealed)	356	°F	ISO 75-2/A
Glass Transition Temperature ²	122	°F	ISO 11357-2
Melting Temperature ²	437	°F	ISO 11357-3
CLTE - Flow	2.3E-5	in/in/°F	ISO 11359-2
CLTE - Transverse	4.1E-5	in/in/°F	ISO 11359-2

Celanex® 5202

Celanese Corporation - Polybutylene Terephthalate

Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	4.0E+15	ohms	IEC 60093
Volume Resistivity	7.0E+16	ohms·cm	IEC 60093
Electric Strength	430	V/mil	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	2.70		
1 MHz	2.70		
Dissipation Factor (1 MHz)	0.014		IEC 60250
Comparative Tracking Index	225	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.031 in)	HB		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	248 to 266	°F
Drying Time	4.0	hr
Suggested Max Moisture	0.020	%
Hopper Temperature	68 to 122	°F
Rear Temperature	446 to 482	°F
Middle Temperature	455 to 491	°F
Front Temperature	455 to 491	°F
Nozzle Temperature	482 to 509	°F
Processing (Melt) Temp	455 to 509	°F
Mold Temperature	149 to 199	°F
Injection Rate	Moderate-Fast	

Injection Notes

Die Temperature: 250 to 265°C
Feed Temperature: 230 to 250°C
Zone 4 Temperature: 240 to 260°C

Notes

¹ Typical properties: these are not to be construed as specifications.

² 10°C/min