



Celanex® 6035GB20

Celanese Corporation - Polybutylene Terephthalate

Monday, November 4, 2019

General Information

Product Description

Celanex 6035GB20 is a 20% glass bead filled PBT.

General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Bead, 20% Filler by Weight
RoHS Compliance	• Contact Manufacturer

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.46	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (250°C/2.16 kg)	15	g/10 min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.5	%	
Flow	1.5	%	
Water Absorption (Equilibrium, 73°F, 50% RH)	0.19	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	479000	psi	ISO 527-2/1A
Tensile Stress (Break)	6670	psi	ISO 527-2/1A/5
Tensile Strain (Break)	8.5	%	ISO 527-2/1A/5
Flexural Modulus (73°F)	479000	psi	ISO 178
Flexural Stress (73°F)	11600	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F	1.3	ft·lb/in ²	
73°F	0.81	ft·lb/in ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F	9.0	ft·lb/in ²	
73°F	10	ft·lb/in ²	
Notched Izod Impact Strength (73°F)	1.7	ft·lb/in ²	ISO 180/1A
Unnotched Izod Impact Strength (73°F)	7.3	ft·lb/in ²	ISO 180/1U
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, 15 sec)	80		ISO 868
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (66 psi, Unannealed)	334	°F	ISO 75-2/B
Heat Deflection Temperature (264 psi, Unannealed)	162	°F	ISO 75-2/A
Glass Transition Temperature ²	122	°F	ISO 11357-2
Melting Temperature ²	437	°F	ISO 11357-3
CLTE - Flow	4.3E-5	in/in/°F	ISO 11359-2
CLTE - Transverse	4.3E-5	in/in/°F	ISO 11359-2

Celanex® 6035GB20

Celanese Corporation - Polybutylene Terephthalate

Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+17	ohms	IEC 60093
Volume Resistivity	3.0E+16	ohms·cm	IEC 60093
Electric Strength	760	V/mil	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	3.70		
1 MHz	3.50		
Dissipation Factor (1 MHz)	0.017		IEC 60250
Comparative Tracking Index	275	V	IEC 60112

Processing Information

Injection	Nominal Value	Unit
Suggested Max Regrind	25	%
Hopper Temperature	68 to 122	°F
Rear Temperature	446 to 464	°F
Middle Temperature	455 to 482	°F
Front Temperature	455 to 482	°F
Nozzle Temperature	482 to 500	°F
Processing (Melt) Temp	455 to 500	°F
Mold Temperature	149 to 199	°F
Injection Rate	Fast	
Back Pressure	0.00 to 50.0	psi

Injection Notes

Die Temperature: 250 to 260°C
Feed Temperature: 230 to 240°C
Zone 4 Temperature: 240 to 260°C

Notes

¹ Typical properties: these are not to be construed as specifications.

² 10°C/min