



Celapex® CL 500CA30

Celanese Corporation - Polyetheretherketone

Tuesday, November 5, 2019

General Information

Product Description

Celapex® 500CA30 is an standard flow, 30% carbon fiber reinforced polyether ether ketone (PEEK) for injection molding and extrusion. It has excellent wear resistance, low coefficient of friction and superior chemically resistant to aggressive environments. The typical applications of this product are extrusion stock shapes, and injection molded parts with higher impact, creep, and fatigue.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Carbon Fiber, 30% Filler by Weight		
Features	• Chemical Resistant • Creep Resistant	• Fatigue Resistant • Good Impact Resistance	• Low Friction • Wear Resistant
Processing Method	• Extrusion • Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.40	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (380°C/5.0 kg)	2.3	g/10 min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	0.50	%	
Flow	0.10	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	32600	psi	ISO 527-2/1A/5
Tensile Strain (Break)	3.5	%	ISO 527-2/1A/5
Flexural Modulus (73°F)	3.34E+6	psi	ISO 178
Flexural Stress (73°F)	55100	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	3.3	ft·lb/in ²	ISO 179/1eA
Charpy Unnotched Impact Strength (73°F)	21	ft·lb/in ²	ISO 179/1eU
Notched Izod Impact Strength (73°F)	4.3	ft·lb/in ²	ISO 180/A
Unnotched Izod Impact Strength (73°F)	21	ft·lb/in ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (264 psi, Unannealed)	637	°F	ISO 75-2/A
Glass Transition Temperature ²	289	°F	ISO 11357-2
Melting Temperature ²	649	°F	ISO 11357-3
CLTE - Flow			ISO 11359-2
-- ³	2.8E-6	in/in/°F	
-- ⁴	3.3E-6	in/in/°F	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+5	ohms·cm	IEC 60093

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

Celapex® CL 500CA30

Celanese Corporation - Polyetheretherketone

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	284 to 302	°F
Drying Time	4.0 to 8.0	hr
Suggested Max Moisture	0.030	%
Processing (Melt) Temp	734 to 770	°F
Mold Temperature	338 to 383	°F
Injection Rate	Moderate-Fast	
Back Pressure	< 290	psi

Notes

¹ Typical properties: these are not to be construed as specifications.

² 10°C/min

³ below

⁴ above