



Celstran® PA66-GF40-02P11/15

Celanese Corporation - Polyamide 66

Monday, November 4, 2019

General Information

Product Description

Material code according to ISO 1043-1: PA66 Heat stabilized Nylon 66 reinforced by 40 weight percent long glass fibers. The pellets are cylindrical and normally as well as the embedded fibers 10 mm long. Parts molded of CELSTRAN have outstanding mechanical properties such as high strength and stiffness combined with high heat deflection. The notched impact strength is increased at elevated and low temperatures due to the fiber skeleton built in the parts. The long fiber reinforcement reduces creep significantly. The very isotropic shrinkage in the molded parts minimizes the warpage. Complex parts can be manufactured with high reproducibility by injection molding. Can be used for substituting die cast metal with the advantage of Weight reduction, no corrosion problems, no post treatment.

General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • North America
Filler / Reinforcement	• Long Glass Fiber, 40% Filler by Weight
Additive	• Heat Stabilizer
Features	• Corrosion Resistant • Heat Stabilized • Low Temperature Impact Resistance • Creep Resistant • High Stiffness • Low Warpage • Good Isotropy • High Strength
Uses	• Metal Replacement
RoHS Compliance	• Contact Manufacturer
Forms	• Pellets
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PA66

ASTM & ISO Properties ¹

Physical	Dry	Conditioned	Unit	Test Method
Density	1.46	1.46	g/cm ³	ISO 1183
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	1.99E+6	1.45E+6	psi	ISO 527-2/1A
Tensile Stress (Break)	27600	23200	psi	ISO 527-2/1A/5
Tensile Strain (Break)	1.6	2.0	%	ISO 527-2/1A/5
Flexural Modulus				ISO 178
73°F	1.83E+6	1.45E+6	psi	
176°F	1.16E+6	1.02E+6	psi	
Flexural Stress				ISO 178
73°F	37700	36300	psi	
176°F	36300	30500	psi	
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-22°F	11	--	ft·lb/in ²	
73°F	11	8.6	ft·lb/in ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°F	20	--	ft·lb/in ²	
73°F	19	21	ft·lb/in ²	
Notched Izod Impact Strength				ISO 180/1A
-22°F	17	--	ft·lb/in ²	
73°F	11	8.8	ft·lb/in ²	

Celstran® PA66-GF40-02P11/15

Celanese Corporation - Polyamide 66

Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature 264 psi, Unannealed	491	--	°F	ISO 75-2/A
Heat Deflection Temperature 1160 psi, Unannealed	464	--	°F	ISO 75-2/C
Melting Temperature ²	502	--	°F	ISO 11357-3

Processing Information

Injection	Dry	Unit
Drying Temperature	158 to 176	°F
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.15	%
Hopper Temperature	158 to 176	°F
Rear Temperature	509 to 527	°F
Middle Temperature	527 to 545	°F
Front Temperature	545 to 563	°F
Nozzle Temperature	581 to 599	°F
Processing (Melt) Temp	581 to 599	°F
Mold Temperature	194 to 248	°F
Injection Rate	Moderate	
Back Pressure	< 435	psi

Injection Notes

Feeding zone temperature: 20 to 50°C
 Zone4 temperature: 295 to 305°C
 Hot runner temperature: 300 to 315°C

Notes

¹ Typical properties: these are not to be construed as specifications.

² 10°C/min