



Celstran® PA66-GF50-02 P11

Celanese Corporation - Polyamide 66

Monday, November 4, 2019

General Information

Product Description

Material code according to ISO 1043-1: PA66 Heat stabilized Nylon 66 reinforced by 50 weight percent long glass fibers. The pellets are cylindrical and normally as well as the embedded fibers 11mm long. Parts molded of CELSTRAN have outstanding mechanical properties such as high strength and stiffness combined with high heat deflection. The notched impact strength is increased at elevated and low temperatures due to the fiber skeleton built in the parts. The long fiber reinforcement reduces creep significantly. The very isotropic shrinkage in the molded parts minimizes the warpage. Complex parts can be manufactured with high reproducibility by injection molding. Can be used for substituting die cast metal with the advantage of Weight reduction, no corrosion problems, no post treatment.

General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • North America
Filler / Reinforcement	• Long Glass Fiber, 50% Filler by Weight
Additive	• Heat Stabilizer
Features	• Corrosion Resistant • Heat Stabilized • Low Temperature Impact Resistance • Creep Resistant • High Stiffness • Low Warpage • Good Isotropy • High Strength
Uses	• Metal Replacement
RoHS Compliance	• Contact Manufacturer
Forms	• Pellets
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PA66

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.56	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2.39E+6	psi	ISO 527-2/1A
Tensile Stress (Break)	37700	psi	ISO 527-2/1A/5
Tensile Strain (Break)	2.0	%	ISO 527-2/1A/5
Flexural Modulus (73°F)	2.13E+6	psi	ISO 178
Flexural Stress (73°F)	61600	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	23	ft-lb/in ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Melting Temperature ²	500	°F	ISO 11357-3

Notes

¹ Typical properties: these are not to be construed as specifications.

² 10°C/min