



Celstran® PA66-GF50-02-Natural

Celanese Corporation - Polyamide 66

Monday, November 4, 2019

General Information

Product Description

50 % Long glass fiber reinforced, heat stabilized, Nylon 6/6

General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • North America
Filler / Reinforcement	• Long Glass Fiber, 50% Filler by Weight
Additive	• Heat Stabilizer
Features	• Heat Stabilized
RoHS Compliance	• Contact Manufacturer
Appearance	• Natural Color

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.56	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2.39E+6	psi	ISO 527-2/1A
Tensile Stress (Break)	37700	psi	ISO 527-2/1A/5
Tensile Strain (Break)	2.0	%	ISO 527-2/1A/5
Flexural Modulus			ISO 178
73°F	2.13E+6	psi	
176°F	1.31E+6	psi	
Flexural Stress (73°F)	61600	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F	16	ft·lb/in ²	
73°F	23	ft·lb/in ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F	38	ft·lb/in ²	
73°F	45	ft·lb/in ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (264 psi, Unannealed)	493	°F	ISO 75-2/A
Heat Deflection Temperature (1160 psi, Unannealed)	480	°F	ISO 75-2/C
Melting Temperature ²	502	°F	ISO 11357-3

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	158 to 176	°F
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.18	%
Hopper Temperature	158 to 176	°F
Rear Temperature	545 to 563	°F
Middle Temperature	554 to 572	°F
Front Temperature	572 to 590	°F

Celstran® PA66-GF50-02-Natural

Celanese Corporation - Polyamide 66

Injection	Nominal Value	Unit
Nozzle Temperature	572 to 599	°F
Processing (Melt) Temp	572 to 599	°F
Mold Temperature	176 to 212	°F

Injection Notes

Feeding zone temperature: 20 to 50°C

Zone4 temperature: 300 to 315°C

Notes

¹ Typical properties: these are not to be construed as specifications.

² 10°C/min