



DOW™ HDPE DMDA-8950 NT 7

The Dow Chemical Company - High Density Polyethylene Resin

Tuesday, November 5, 2019

General Information

Product Description

DOW™ DMDA-8950 NT 7 High Density Polyethylene (HDPE) Resin is produced via UNIPOL™ Process Technology from Dow and is intended for use in thin-wall injection molding applications such as food containers, including freezer applications. This resin has been designed to provide a good impact/stiffness balance as well as excellent processability.

Main Characteristics

- Injection molding
- For injection molded thin-wall food containers, including freezer applications
- High flow for processing ease
- Very narrow molecular weight distribution

Complies with:

- U.S. FDA 21 CFR 177.1520(c) 3.2a
- Canadian HPFB No Objection

Consult the regulations for complete details.

General

Material Status	• Commercial: Active
Availability	• North America
Additive	• Antiblock: No • Processing Aid: No • Slip: No
Agency Ratings	• FDA 21 CFR 177.1520(c) 3.2a • HPFB (Canada) No Objection
Forms	• Pellets

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.944		ASTM D792
Melt Mass-Flow Rate (190°C/2.16 kg)	50	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (ESCR) 122°F, 100% Igepal, F50	6.00	hr	ASTM D1693
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	3030	psi	ASTM D638
Tensile Strength (Break)	2090	psi	ASTM D638
Tensile Elongation (Yield)	9.0	%	ASTM D638
Tensile Elongation (Break)	37	%	ASTM D638
Flexural Modulus - 2% Secant	83500	psi	ASTM D790B
Impact	Nominal Value	Unit	Test Method
Tensile Impact Strength ²	43.0	ft-lb/in ²	ASTM D1822
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-63.0	°F	ASTM D746
Melting Temperature (DSC)	260	°F	Internal Method
Peak Crystallization Temperature (DSC)	239	°F	Internal Method

Additional Information

Plaque molded and tested in accordance with ASTM D 4976.

DOW™ HDPE DMDA-8950 NT 7

The Dow Chemical Company - High Density Polyethylene Resin

Notes

¹ Typical properties: these are not to be construed as specifications.

² Type S