



DOW™ LDPE 503A

The Dow Chemical Company - Low Density Polyethylene Resin

Tuesday, November 5, 2019

General Information

Product Description

- A slip and Antiblock additive resin for liners, industrial and clarity
- Optimum gauge range: 1.0-3.0 mil
- Complies with U.S. FDA 21 CFR 177.1520(c)2.2.
- Complies with Canadian HPFB No Objection (With Limitations)
- Complies with EU, No 10/2011
- Consult the regulations for complete details.

General

Material Status	• Commercial: Active		
Availability	• Latin America	• North America	
Additive	• Antiblock: 1200 ppm	• Processing Aid: No	• Slip: 750 ppm
Agency Ratings	• EU No 10/2011	• FDA 21 CFR 177.1520(c) 2.2	• HPFB (Canada) No Objection ¹
Forms	• Pellets		
Processing Method	• Blown Film		

ASTM & ISO Properties ²

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.925		ASTM D792
Melt Mass-Flow Rate (190°C/2.16 kg)	1.9	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	2	mil	
Film Puncture Resistance (2.0 mil)	34.0	ft·lb/in ³	Internal Method
Film Toughness - MD (2.0 mil)	2220	ft·lb/in ³	ASTM D882
Film Toughness - TD (2.0 mil)	2290	ft·lb/in ³	ASTM D882
Tensile Strength - MD (Yield, 2.0 mil)	1740	psi	ASTM D882
Tensile Strength - TD (Yield, 2.0 mil)	1780	psi	ASTM D882
Tensile Strength - MD (Break, 2.0 mil)	3600	psi	ASTM D882
Tensile Strength - TD (Break, 2.0 mil)	3010	psi	ASTM D882
Tensile Elongation - MD (Break, 2.0 mil)	520	%	ASTM D882
Tensile Elongation - TD (Break, 2.0 mil)	720	%	ASTM D882
Dart Drop Impact (2.0 mil)	100	g	ASTM D1709A
Elmendorf Tear Strength - MD (2.0 mil)	560	g	ASTM D1922
Elmendorf Tear Strength - TD (2.0 mil)	470	g	ASTM D1922
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	198	°F	ASTM D1525
Melting Temperature (DSC)	232	°F	Internal Method
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 2.00 mil)	70		ASTM D2457
Haze (2.00 mil)	7.50	%	ASTM D1003

Processing Information

Extrusion	Nominal Value	Unit
Melt Temperature	422	°F

DOW™ LDPE 503A

The Dow Chemical Company - Low Density Polyethylene Resin

Extrusion Notes

Fabrication Conditions For Blown Film:

- Screw Size: 2.5 in. (63.5 mm); 30:1 L/D
- Screw Type: Single Flight Double Mix
- Die Gap: 40 mil (1.02 mm)
- Melt Temperature: 422°F (217°C)
- Output: 10 lb/hr/in. of die circumference
- Die Diameter: 6 in.
- Blow-Up Ratio: 2.5:1
- Screw Speed: 92 rpm
- Frost Line Height: 30 in. (792 mm)

Notes

¹ With limitations

² Typical properties: these are not to be construed as specifications.
