

DOW™ LLDPE DNDA-1081 NT 7

The Dow Chemical Company - Linear Low Density Polyethylene Resin

Tuesday, November 5, 2019

General Information

Product Description

- · Injection molding
- Lids
- · Excellent processability with good low temperature impact strength and rigidity
- · Very narrow molecular weight distribution
- Complies with U.S. FDA 21 CFR 177.1520 (c)3.1a
- · Complies with FDA-DMF
- Complies with EU, No 10/2011
- · Complies with CANADIAN HPFB NO OBJECTION (WITH LIMITATIONS)
- · Consult the regulations for complete details.

DOW DNDA-1081 NT 7 Linear Low Density Polyethylene (LLDPE) Resin is produced using UNIPOL™ PE Process Technology and is intended for highspeed injection molding of thin-walled parts such as downgauged lids. This resin has been designed to have an excellent balance of processability, impact strength, and rigidity.

General			
Material Status	Commercial: Active		
Availability	Latin America	North America	
Agency Ratings	 DMF Unspecified Rating 	• FDA 21 CFR 177.1520(c) 3.1a	
	• EU No 10/2011	 HPFB (Canada) No Objection ¹ 	
Forms	 Pellets 		
Processing Method	Injection Molding		

ASTM & ISO Properties ²					
Physical	Nominal Value	Unit	Test Method		
Density / Specific Gravity	0.933		ASTM D792		
Melt Mass-Flow Rate (190°C/2.16 kg)	128	g/10 min	ASTM D1238		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength (Yield)	1600	psi	ASTM D638		
Tensile Strength (Break)	1300	psi	ASTM D638		
Tensile Elongation (Yield)	2.0	%	ASTM D638		
Tensile Elongation (Break)	60	%	ASTM D638		
Flexural Modulus - 2% Secant	76000	psi	ASTM D790B		
Impact	Nominal Value	Unit	Test Method		
Tensile Impact Strength ³	50.0	ft·lb/in²	ASTM D1822		
Hardness	Nominal Value	Unit	Test Method		
Durometer Hardness (Shore D)	55		ASTM D2240		
Thermal	Nominal Value	Unit	Test Method		
Deflection Temperature Under Load (66 psi, Unannealed)	124	°F	ASTM D648		
Brittleness Temperature	-11.0	°F	ASTM D746		
Vicat Softening Temperature	207	°F	ASTM D1525		
Melting Temperature (DSC)	259	°F	Internal Method		
Peak Crystallization Temperature (DSC)	235	°F	Internal Method		
Additional Information					

Plaque molded and tested in accordance with ASTM D4976.



DOW™ LLDPE DNDA-1081 NT 7

The Dow Chemical Company - Linear Low Density Polyethylene Resin

Notes

¹ With limitations

 $^{\rm 2}$ Typical properties: these are not to be construed as specifications.

³ Type S

