



# DOWLEX™ GM 8051G

The Dow Chemical Company - Polyethylene Resin

Tuesday, November 5, 2019

## General Information

### Product Description

DOWLEX™ GM 8051G Polyethylene Resin is designed for use in a wide variety of film applications, in special for FFS and lamination multilayered films combining excellent optical properties, mechanicals and an additive package designed to enhance COF stability.

#### Main Characteristics

- High toughness, processability and optical properties
- Fully formulated, enhanced COF stability

#### Complies with:

- U.S. FDA FCN 741

Consult the regulations for complete details.

#### Additives:

- Slip: Yes
- Antiblock: Yes

### General

|                 |                                                            |
|-----------------|------------------------------------------------------------|
| Material Status | • Commercial: Active                                       |
| Availability    | • Europe • Latin America • North America                   |
| Additive        | • Antiblock: 2500 ppm • Processing Aid: No • Slip: 900 ppm |
| Agency Ratings  | • FDA FCN 741                                              |
| Forms           | • Pellets                                                  |

## ASTM & ISO Properties <sup>1</sup>

| Physical                            | Nominal Value | Unit                  | Test Method     |
|-------------------------------------|---------------|-----------------------|-----------------|
| Density                             | 0.921         | g/cm <sup>3</sup>     | ASTM D792       |
| Melt Mass-Flow Rate (190°C/2.16 kg) | 0.90          | g/10 min              | ASTM D1238      |
| Films                               | Nominal Value | Unit                  | Test Method     |
| Film Thickness - Tested             | 2             | mil                   |                 |
| Film Puncture Resistance            | 346           | ft-lb/in <sup>3</sup> | Internal Method |
| Secant Modulus - 2% Secant, MD      | 25800         | psi                   |                 |
| Secant Modulus - 2% Secant, TD      | 29400         | psi                   |                 |
| Tensile Strength - MD (Yield)       | 1040          | psi                   | ASTM D882       |
| Tensile Strength - TD (Yield)       | 1070          | psi                   | ASTM D882       |
| Tensile Strength - MD (Break)       | 6290          | psi                   | ASTM D882       |
| Tensile Strength - TD (Break)       | 5700          | psi                   | ASTM D882       |
| Tensile Elongation - MD (Break)     | 830           | %                     | ASTM D882       |
| Tensile Elongation - TD (Break)     | 850           | %                     | ASTM D882       |
| Dart Drop Impact                    | 600           | g                     | ASTM D1709A     |
| Elmendorf Tear Strength - MD        | 740           | g                     | ASTM D1922      |
| Elmendorf Tear Strength - TD        | 890           | g                     | ASTM D1922      |
| Thermal                             | Nominal Value | Unit                  | Test Method     |
| Vicat Softening Temperature         | 226           | °F                    | ASTM D1525      |
| Melting Temperature (DSC)           | 250           | °F                    | Internal Method |

# DOWLEX™ GM 8051G

## The Dow Chemical Company - Polyethylene Resin

| Optical               | Nominal Value | Unit | Test Method |
|-----------------------|---------------|------|-------------|
| Gloss (45°, 1.97 mil) | 63            |      | ASTM D2457  |
| Haze (1.97 mil)       | 11.4          | %    | ASTM D1003  |

### Processing Information

#### Extrusion Notes

Fabrication Conditions For Blown Film:

- Machine: Monolayer blown film extrusion line
- Monolayer Film (50 microns)
- Screw Size: 25 mm 25:1 L/D
- Die Gap: 1.8 mm
- Output: 15 kg/hr
- Die Diameter: 80mm
- Blow-up Ratio: 2.5 : 1

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.