



Elvaloy® AC 1125

DuPont Packaging & Industrial Polymers - Ethylene Methyl Acrylate Copolymer

Sunday, November 3, 2019

General Information

Product Description

Elvaloy® AC 1125 is a copolymer of ethylene and methyl acrylate. It is available in pellet form for use in conventional extrusion equipment designed to process polyethylene type resins.

25% By Weight Methyl Acrylate

General

Material Status	• Commercial: Active
Availability	• Europe • North America
Features	• Copolymer • High ESCR (Stress Crack Resist.) • Good Flexibility • Soft
Agency Ratings	• FDA 21 CFR 175.105
Forms	• Pellets
Processing Method	• Blow Molding • Coextrusion

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.946		ASTM D792
Density	0.944	g/cm ³	ISO 1183
Melt Mass-Flow Rate (190°C/2.16 kg)	0.50	g/10 min	ASTM D1238
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.50	g/10 min	ISO 1133
Methyl Acrylate Content	25.0	wt%	
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	118	°F	ASTM D1525
Vicat Softening Temperature	118	°F	ISO 306
Melting Temperature (DSC)	194	°F	ISO 3146
Melting Temperature	194	°F	DSC

Processing Information

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	275	°F
Cylinder Zone 2 Temp.	320	°F
Cylinder Zone 3 Temp.	365	°F
Cylinder Zone 4 Temp.	365	°F
Cylinder Zone 5 Temp.	365	°F
Adapter Temperature	365	°F
Melt Temperature	320 to 455	°F
Die Temperature	365	°F

Notes

¹ Typical properties: these are not to be construed as specifications.