



Elvaloy® AC 12024S

DuPont Packaging & Industrial Polymers - Ethylene Methyl Acrylate Copolymer

Sunday, November 3, 2019

General Information

Product Description

Elvaloy® AC 12024S is a copolymer of ethylene and methyl acrylate. It is available in pellet form for use in conventional extrusion equipment designed to process polyethylene type resins.

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • Asia Pacific • Latin America • North America
Additive	• Antioxidant
Features	• Antioxidant
Agency Ratings	• FDA 21 CFR 177.1340(a)
Forms	• Pellets
Processing Method	• Extrusion

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.946		ASTM D792
Density	0.944	g/cm ³	ISO 1183
Melt Mass-Flow Rate (190°C/2.16 kg)	20	g/10 min	ASTM D1238
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	20	g/10 min	ISO 1133
Methyl Acrylate Content	24.0	wt%	
Thermal	Nominal Value	Unit	Test Method
Peak Melting Temperature	190	°F	ASTM D3418
Melting Temperature (DSC)	190	°F	ISO 3146

Processing Information

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	320	°F
Cylinder Zone 2 Temp.	410	°F
Cylinder Zone 3 Temp.	455	°F
Cylinder Zone 4 Temp.	455	°F
Cylinder Zone 5 Temp.	455	°F
Adapter Temperature	455	°F
Melt Temperature	410 to 500	°F
Die Temperature	455	°F

Notes

¹ Typical properties: these are not to be construed as specifications.