



Elvaloy® AC 2618

DuPont Packaging & Industrial Polymers - Ethylene Ethyl Acrylate Copolymer

Sunday, November 3, 2019

General Information

Product Description

Elvaloy® AC 2618 is a copolymer of ethylene and ethyl acrylate. It is available in pellet form for use in conventional extrusion equipment designed to process polyethylene type resins.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Agency Ratings	• FDA 21 CFR 177.1320(a)		
Forms	• Pellets		
Processing Method	• Extrusion		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.932		ASTM D792
Density	0.930	g/cm ³	ISO 1183
Melt Mass-Flow Rate (190°C/2.16 kg)	6.0	g/10 min	ASTM D1238
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	6.0	g/10 min	ISO 1133
Ethyl Acrylate Content	18.0	wt%	
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	133	°F	ASTM D1525
Vicat Softening Temperature	133	°F	ISO 306
Peak Melting Temperature	203	°F	ASTM D3418
Melting Temperature (DSC)	203	°F	ISO 3146

Processing Information

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	365	°F
Cylinder Zone 2 Temp.	455	°F
Cylinder Zone 3 Temp.	500	°F
Cylinder Zone 4 Temp.	545	°F
Cylinder Zone 5 Temp.	545	°F
Adapter Temperature	545	°F
Melt Temperature	455 to 590	°F
Die Temperature	545	°F

Notes

¹ Typical properties: these are not to be construed as specifications.