

EnViramid® N2330HL BK

Ravago Manufacturing Americas - Polyamide 6

Monday, November 4, 2019

General Information					
Product Description					
Nylon 6, 30% Glass Filled					
General					
Material Status	Commercial: Active				
Availability	North America				
Filler / Reinforcement	Glass Fiber, 30% Filler by Weight				
Recycled Content	• Yes				
RoHS Compliance	RoHS Compliant				
UL File Number	• E157012				

ASTM & ISO Properties 1						
Physical	Dry	Conditioned	Unit	Test Method		
Density	1.39	-	g/cm³	ISO 1183		
Molding Shrinkage - Flow (0.125 in)	0.10 to 0.50		%	ISO 294-4		
Mechanical	Dry	Conditioned	Unit	Test Method		
Tensile Stress (Break)	20000	12300	psi	ISO 527-2		
Tensile Strain (Break)	3.0	5.0	%	ISO 527-2		
Flexural Modulus	1.42E+6	895000	psi	ISO 178		
Flexural Stress	29000	18300	psi	ISO 178		
Impact	Dry	Conditioned	Unit	Test Method		
Charpy Notched Impact Strength	5.2	7.6	ft·lb/in²	ISO 179		
Notched Izod Impact Strength	5.2	7.6	ft·lb/in²	ISO 180		
Thermal	Dry	Conditioned	Unit	Test Method		
Heat Deflection Temperature				ISO 75-2/A		
264 psi, Unannealed	394		°F			
Flammability	Dry	Conditioned	Unit	Test Method		
Flame Rating (0.06 in)	НВ			UL 94		

Notes



¹ Typical properties: these are not to be construed as specifications.