

**FLEXIRENE[®]**

LLDPE

MS 40 U

Linear low density polyethylene

Flexirene MS 40 U is a linear low density polyethylene (LLDPE) with antioxidants, suitable for injection moulding application.

Parts made by Flexirene MS 40 U are characterised by a good balance between impact resistance and rigidity.

Main applications

Flexirene MS 40 U is recommended for the production of large sized articles, houseware and toys. Flexirene MS 40 U is characterized by a high flowability which make it ideal for masterbatches preparation for LDPE and LLDPE.

Main properties

Resin Properties	Test method	Unit	Value
Melt Flow Rate (190 °C/ 2.16 kg)	ISO 1133	g/10min	27
Density	ISO 1183	g/cm ³	0.930
Melting point	Internal method	°C	123
Brittleness point	ASTM D 746	°C	< - 70
Vicat softening point (1 kg)	ISO 306/A	°C	103

Mechanical Properties *	Test method	Unit	Value
Tensile stress at yield	ISO 527	MPa	11
Tensile strenght at break	ISO 527	MPa	12
Elongation at break	ISO 527	%	> 500
Flexural modulus	ISO 178	MPa	300
Hardness Shore D	ISO 868/A		52

* Values are referred to injection moulded specimens. Actual properties are typical and may vary depending upon operating conditions.

Processing conditions

Flexirene MS 40 U is easy to mould with the newest injection moulding machines. Results are excellent.
Typical processing conditions (*)
Temperature profile of the barrel (°C) 160 - 210
Temperature of the mould (°C) 10 - 40
(*) Processing conditions are depending on several parameters: the shape of the part to be manufactured, the localisation of the injection point, the injection moulding machine and the cooling of the mould.

Storage and handling

Flexirene MS 40 U is supplied in pellet form. This material may readily be conveyed and bulk fed through equipment designed for conventional pelletised polyethylene resin, provided the equipment is designed to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping be practised throughout your facility.
Stored in an airy and dry room, at temperatures between 20°C and 30°C, with no direct sunlight, the shelf life is about 18 months. However, before using this product, read and understand the relevant POLIMERI EUROPA Safety Data Sheet.

Availability

Contact the POLIMERI EUROPA sales office nearest to you regarding availability and your specific application requirements.

Food contact status

Flexirene MS 40 U complies with the rules and regulations of the European Union, as well as other countries, regarding the use of plastic materials in food contact applications. Certificates of compliance are available upon request.

TECHNICAL SERVICE

Polimeri Europa S.p.A.
Piazza Boldrini, 1
20097 S. Donato Milanese, Italia
Tel. +39 02 520.1
Fax + 39 02 520.42901

Polimeri Europa SAS
1 Route des Dunes BP 59
F-59279 MARDYCK - France
Tel. +33 3 28235514
Fax +33 3 28235520

Polimeri Europa S.p.A.
Via Taliercio, 14
46100 Mantova, Italia
Tel. +39 0376 305504
Fax + 39 0376 305299

HEADQUARTER

Polimeri Europa S.p.A.
Piazza Boldrini, 1
20097 San Donato Milanese, Milano - Italia
Tel. +39 02 520.1
Fax + 39 02 520.42901

IMPORTANT: please consult the relevant safety data sheet for more detailed information. The information and data presented herein are to the best of our knowledge true and accurate but no warranty or guarantee, expressed or implied, is made nor is any liability accepted with respect to the use of such information and data.
Polimeri europa is available to provide the guaranteed values for each product on demand.
