

# Formolene® FR150BW

## Formosa Plastics Corporation, U.S.A. - Low Density Polyethylene

Tuesday, November 5, 2019

### **General Information**

#### **Product Description**

Formolene ® FR150BW is a low density polyethylene with films exhibiting good stiffness and optical properties. This LDPE grade offers good mechanical properties in blends.

Formolene ® FR150BW is formulated without slip and antiblock for use in film applications offering excellent extrusion processing and very good balance of mechanical and optical properties.

General				
Material Status	Commercial: Active			
Availability	North America			
Features	<ul><li>Excellent Processability</li><li>Good Optical Properties</li></ul>	<ul><li>Good Stiffness</li><li>Low Density</li></ul>		
Uses	<ul><li>Agricultural Applications</li><li>Blending</li></ul>	<ul><li>Film</li><li>Laminates</li></ul>	Shrink Wrap	
Agency Ratings	• EC 1907/2006 (REACH)			
Processing Method	Coextrusion	• Extrusion	Film Extrusion	

ASTM & ISO Properties <sup>1</sup>				
Physical	Nominal Value	Unit	Test Method	
Density	0.923	g/cm³	ASTM D1505	
Melt Mass-Flow Rate (190°C/2.16 kg)	0.75	g/10 min	ASTM D1238	
Films	Nominal Value	Unit	Test Method	
Film Thickness - Tested	2	mil		
Secant Modulus - 1% Secant, MD (2.0 mil, Blown Film)	35000	psi	ASTM D882	
Secant Modulus - 1% Secant, TD (2.0 mil, Blown Film)	40000	psi	ASTM D882	
Tensile Strength - MD (Break, 2.0 mil, Blown Film)	4000	psi	ASTM D882	
Tensile Strength - TD (Break, 2.0 mil, Blown Film)	3200	psi	ASTM D882	
Tensile Elongation - MD (Break, 2.0 mil, Blown Film)	310	%	ASTM D882	
Tensile Elongation - TD (Break, 2.0 mil, Blown Film)	530	%	ASTM D882	
Dart Drop Impact (2.0 mil, Blown Film)	180	g	ASTM D1709	
Elmendorf Tear Strength - MD (2.0 mil, Blown Film)	350	g	ASTM D1922	
Elmendorf Tear Strength - TD (2.0 mil, Blown Film)	150	g	ASTM D1922	
Optical	Nominal Value	Unit	Test Method	
Gloss (45°, 1.97 mil, Blown Film)	59		ASTM D2457	
Haze (1.97 mil, Blown Film)	8.40	%	ASTM D1003	

Processing Information		
Extrusion	Nominal Value Unit	
Melt Temperature	356 to 374 °F	

#### **Notes**



<sup>&</sup>lt;sup>1</sup> Typical properties: these are not to be construed as specifications.