

Fusabond® A560

DuPont Packaging & Industrial Polymers - Ethylene Acrylate Copolymer

Sunday, November 3, 2019

General Information					
Product Description					
DuPont™ Fusabond® A560 i	s a chemically modified ethylene acrylate co	ppolymer			
General					
Material Status	Commercial: Active				
Availability	 Africa & Middle East Asia Pacific	EuropeLatin America	North America		
Uses	 Plastics Modification 				
Forms	Pellets				

ASTM & ISO Properties 1					
Physical	Nominal Value Un	nit	Test Method		
Density / Specific Gravity	0.932		ASTM D792		
Density	0.930 g/c	cm³	ISO 1183		
Melt Mass-Flow Rate (190°C/2.16 kg)	5.6 g/1	10 min	ASTM D1238		
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	5.6 g/1	10 min	ISO 1133		
Thermal	Nominal Value Un	nit	Test Method		
Peak Melting Temperature	201 °F		ASTM D3418		
Melting Temperature (DSC)	201 °F		ISO 3146		
Additional Information	Nominal Value Un	nit			
Processing Temperature	< 500 °F				

Notes

¹ Typical properties: these are not to be construed as specifications.