



HYLEX® P1025L2V2 FDA

Entec Polymers - Polycarbonate

Monday, November 4, 2019

General Information

Product Description

POLYCARBONATE, HIGH MELT FLOW, UL94 V2, FDA FOOD CONTACT

General

Material Status	• Commercial: Active
Availability	• North America
Features	• Food Contact Acceptable • High Flow
Agency Ratings	• FDA Food Contact, Unspecified Rating

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.20		ASTM D792
Melt Mass-Flow Rate (300°C/1.2 kg)	25	g/10 min	ASTM D1238
Molding Shrinkage - Flow	5.0E-3 to 7.0E-3	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break, 73°F)	9500	psi	ASTM D638
Tensile Elongation (Break, 73°F)	120	%	ASTM D638
Flexural Modulus (73°F)	335000	psi	ASTM D790
Flexural Strength (73°F)	13500	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	12	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 264 psi, Unannealed	260	°F	ASTM D648
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-2		UL 94

Notes

¹ Typical properties: these are not to be construed as specifications.