



HYLEX® P1318FRVNHE

Ravago Manufacturing Americas - Polycarbonate

Monday, November 4, 2019

General Information

Product Description

Polycarbonate, Flame Retardant, Non Halogenated

General

Material Status	• Commercial: Active
Availability	• North America
Additive	• Flame Retardant
Features	• Flame Retardant • Halogen Free
RoHS Compliance	• RoHS Compliant
UL File Number	• E157012

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ISO 1183
Melt Mass-Flow Rate (300°C/1.2 kg)	18	g/10 min	ASTM D1238
Molding Shrinkage - Flow (0.125 in)	0.50 to 0.70	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	8700	psi	ISO 527-2
Tensile Strain (Break)	20	%	ISO 527-2
Flexural Modulus	325000	psi	ISO 178
Flexural Stress	14100	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	20	ft·lb/in ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (66 psi, Unannealed)	280	°F	ISO 75-2/B
Heat Deflection Temperature (264 psi, Unannealed)	266	°F	ISO 75-2/A
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.06 in		V-0	
0.12 in	•	V-0	
	•	5VA	

Notes

¹ Typical properties: these are not to be construed as specifications.