

HYLON® N1015STHL

Ravago Manufacturing Americas - Polyamide 66

Monday, November 4, 2019

| General Information | | | |
|---------------------------------|-----------------------------------|--|--|
| Product Description | | | |
| Nylon 66, 15% Glass Filled, Sup | erior Toughness | | |
| General | | | |
| Material Status | Commercial: Active | | |
| Availability | North America | | |
| Filler / Reinforcement | Glass Fiber, 15% Filler by Weight | | |
| Features | High Toughness | | |
| RoHS Compliance | RoHS Compliant | | |
| UL File Number | • E157012 | | |

| ASTM & ISO Properties ¹ | | | | |
|---|---------------|-----------|-------------|--|
| Physical | Nominal Value | Unit | Test Method | |
| Density | 1.19 | g/cm³ | ISO 1183 | |
| Mechanical | Nominal Value | Unit | Test Method | |
| Tensile Stress (Break) | 13100 | psi | ISO 527-2 | |
| Tensile Strain (Break) | 3.0 | % | ISO 527-2 | |
| Flexural Modulus | 540000 | psi | ISO 178 | |
| Flexural Stress | 20000 | psi | ISO 178 | |
| Impact | Nominal Value | Unit | Test Method | |
| Charpy Notched Impact Strength | 7.1 | ft·lb/in² | ISO 179 | |
| Notched Izod Impact Strength | 7.1 | ft·lb/in² | ISO 180 | |
| Thermal | Nominal Value | Unit | Test Method | |
| Heat Deflection Temperature (264 psi, Unannealed) | 441 | °F | ISO 75-2/A | |

Notes

¹ Typical properties: these are not to be construed as specifications.