

HYLON® N1030HLBK

Ravago Manufacturing Americas - Polyamide 66

Monday, November 4, 2019

General Information			
Product Description			
Nylon 66, 30% Glass Filled, Blac	ck		
General			
Material Status	Commercial: Active		
Availability	North America		
Filler / Reinforcement	Glass Fiber, 30% Filler by Weight		
RoHS Compliance	RoHS Compliant		
UL File Number	• E157012		
Appearance	Black		

ASTM & ISO Properties ¹				
Physical	Nominal Value	Unit	Test Method	
Density	1.37	g/cm³	ISO 1183	
Molding Shrinkage - Flow (0.125 in)	0.30 to 0.50	%	ISO 294-4	
Water Absorption (24 hr, 73°F)	0.70	%	ISO 62	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Stress (Break)	24700	psi	ISO 527-2	
Tensile Strain (Break)	2.0	%	ISO 527-2	
Flexural Modulus	1.23E+6	psi	ISO 178	
Flexural Stress	37300	psi	ISO 178	
Impact	Nominal Value	Unit	Test Method	
Charpy Notched Impact Strength	3.8	ft·lb/in²	ISO 179	
Notched Izod Impact Strength	3.8	ft·lb/in²	ISO 180	
Thermal	Nominal Value	Unit	Test Method	
Heat Deflection Temperature (264 psi, Unannealed)	469	°F	ISO 75-2/A	
Flammability	Nominal Value	Unit	Test Method	
Flame Rating (0.06 in)	НВ		UL 94	

Notes



¹ Typical properties: these are not to be construed as specifications.