



HYLON® N2030GBHL

Ravago Manufacturing Americas - Polyamide 6

Monday, November 4, 2019

General Information

Product Description

Nylon 6, 30% Glass Beads

General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Bead, 30% Filler by Weight
RoHS Compliance	• RoHS Compliant
UL File Number	• E157012

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.36	g/cm ³	ISO 1183
Molding Shrinkage - Flow (0.125 in)	0.11 to 0.15	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	8120	psi	ISO 527-2
Tensile Strain (Break)	2.5	%	ISO 527-2
Flexural Modulus	560000	psi	ISO 178
Flexural Stress	16700	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	1.4	ft-lb/in ²	ISO 179
Notched Izod Impact Strength	1.4	ft-lb/in ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (264 psi, Unannealed)	216	°F	ISO 75-2/A

Notes

¹ Typical properties: these are not to be construed as specifications.