



Impet® 2700 GV1/45 (Europe)

Celanese Corporation - Polyethylene Terephthalate

Tuesday, November 5, 2019

General Information

Product Description

Polyethylene terephthalate, 45 % glass filled, high flowability, excellent gloss, high modulus, very high heat deflection temperature.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass Fiber, 45% Filler by Weight		
Features	• High Flow	• High Gloss	• High Stiffness
RoHS Compliance	• Contact Manufacturer		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.74	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (280°C/2.16 kg)	4.0	g/10 min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	0.60	%	
Flow	0.20	%	
Water Absorption (Saturation, 73°F)	0.40	%	ISO 62
Water Absorption (Equilibrium, 73°F, 50% RH)	0.15	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2.47E+6	psi	ISO 527-2/1A
Tensile Stress (Break)	26800	psi	ISO 527-2/1A/5
Tensile Strain (Break)	1.5	%	ISO 527-2/1A/5
Flexural Modulus (73°F)	2.47E+6	psi	ISO 178
Flexural Stress (73°F)	34800	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F	6.2	ft·lb/in ²	
73°F	5.7	ft·lb/in ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F	15	ft·lb/in ²	
73°F	17	ft·lb/in ²	
Notched Izod Impact Strength (73°F)	6.2	ft·lb/in ²	ISO 180/1A
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	121		ISO 2039-2
Ball Indentation Hardness ²	43500	psi	ISO 2039-1
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (66 psi, Unannealed)	486	°F	ISO 75-2/B
Heat Deflection Temperature (264 psi, Unannealed)	442	°F	ISO 75-2/A
Heat Deflection Temperature (1160 psi, Unannealed)	338	°F	ISO 75-2/C
Vicat Softening Temperature	500	°F	ISO 306/B50
Melting Temperature ³	478	°F	ISO 11357-3
CLTE - Flow	8.3E-6	in/in/°F	ISO 11359-2

Impet® 2700 GV1/45 (Europe)

Celanese Corporation - Polyethylene Terephthalate

Thermal	Nominal Value	Unit	Test Method
CLTE - Transverse	5.6E-5	in/in/°F	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+16	ohms·cm	IEC 60093
Electric Strength	890	V/mil	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	5.20		
1 MHz	4.50		
Dissipation Factor			IEC 60250
100 Hz	3.0E-3		
1 MHz	0.017		
Arc Resistance	110	sec	Internal Method
Comparative Tracking Index	175	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.031 in	HB		
0.06 in	HB		
Oxygen Index	26	%	ISO 4589-2

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	248 to 284	°F
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.010	%
Hopper Temperature	68 to 122	°F
Rear Temperature	500 to 518	°F
Middle Temperature	518 to 536	°F
Front Temperature	536 to 554	°F
Nozzle Temperature	518 to 554	°F
Processing (Melt) Temp	518 to 554	°F
Mold Temperature	275 to 293	°F
Injection Rate	Fast	

Injection Notes

Feeding zone temperature: 40 to 60°C

Zone4 temperature: 280 to 290°C

Hot runner temperature: 270 to 290°C

Notes

¹ Typical properties: these are not to be construed as specifications.

² 30s

³ 10°C/min