



POLYLAC® PA-709P

CHI MEI CORPORATION - Acrylonitrile Butadiene Styrene

Sunday, November 3, 2019

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Uses	• Piping		
RoHS Compliance	• RoHS Compliant		
Processing Method	• Pipe Extrusion		
Resin ID (ISO 1043)	• >ABS<		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity ²	1.04		ASTM D792
Density (73°F)	1.04	g/cm ³	ISO 1183
Melt Mass-Flow Rate (200°C/5.0 kg)	0.50	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	5.00	cm ³ /10min	ISO 1133
Molding Shrinkage	0.40 to 0.70	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ³ (Yield)	6530	psi	ASTM D638
Tensile Stress (Yield)	6090	psi	ISO 527-2/50
Tensile Stress (Break)	4500	psi	ISO 527-2/50
Tensile Elongation ³ (Break)	50	%	ASTM D638
Tensile Strain (Break)	30	%	ISO 527-2/50
Flexural Modulus ⁴	300000	psi	ASTM D790
Flexural Modulus ⁵	290000	psi	ISO 178
Flexural Strength ⁴	9200	psi	ASTM D790
Flexural Stress ⁵	8850	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	19	ft-lb/in ²	ISO 179
Notched Izod Impact (73°F, 0.252 in)	6.8	ft-lb/in	ASTM D256
Notched Izod Impact Strength (73°F)	19	ft-lb/in ²	ISO 180/1A
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	100		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 264 psi, Unannealed	190	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Annealed)	208	°F	ASTM D648
Heat Deflection Temperature (264 psi, Annealed)	208	°F	ISO 75-2/A
Vicat Softening Temperature	219	°F	ASTM D1525 ⁶
Vicat Softening Temperature --	223	°F	ISO 306/A50
--	214	°F	ISO 306/B50
CLTE - Flow	4.8E-5	in/in/°F	ISO 11359-2

POLYLAC® PA-709P

CHI MEI CORPORATION - Acrylonitrile Butadiene Styrene

Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	HB		UL 94

Processing Information

Extrusion	Nominal Value	Unit
Drying Temperature	176 to 185	°F
Drying Time	2.0 to 4.0	hr
Cylinder Zone 1 Temp.	374 to 410	°F
Cylinder Zone 3 Temp.	410 to 464	°F
Cylinder Zone 5 Temp.	428 to 482	°F
Die Temperature	392 to 482	°F

Notes

¹ Typical properties: these are not to be construed as specifications.

² 23°C

³ 0.24 in/min

⁴ 0.11 in/min

⁵ 0.079 in/min

⁶ Rate A (50°C/h), Loading 1 (10 N)