

# PRIMEVA® P28800

# **REPSOL - Ethylene Vinyl Acetate Copolymer**

Sunday, November 3, 2019

### **General Information**

#### **Product Description**

EVA resin REPSOL PRIMEVA® P28800 is a very low viscosity copolymer for hot melt adhesives applications. EVA resin REPSOL PRIMEVA® P28800 has been improved for a better stability against thermal degradation. It contains antioxidant and free flowing agent.

# Applications:

- · Hot Melt Adhesives.
  - · Packaging.
  - Bookbinding

Recommended melt temperature below 200°C to avoid the decomposition of the polymer. Processing conditions should be optimised for each production line.

General					
Material Status	Commercial: Active				
Availability	<ul><li> Africa &amp; Middle East</li><li> Asia Pacific</li></ul>	<ul><li>Europe</li><li>Latin America</li></ul>	North America		
Additive	<ul> <li>Antioxidant</li> </ul>	Free Flowing Agent			
Features	<ul><li>Antioxidant</li><li>Copolymer</li></ul>	<ul><li>Food Contact Acceptable</li><li>Good Thermal Stability</li></ul>	Low Viscosity		
Uses	<ul> <li>Adhesives</li> </ul>	Packaging			
Agency Ratings	EU Food Contact, Unspecified Rating				

ASTM & ISO Properties <sup>1</sup>					
Physical	Nominal Value	Unit	Test Method		
Density (73°F)	0.946	g/cm³	ISO 1183		
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	800	g/10 min	ISO 1133		
Vinyl Acetate Content	28.0	wt%	Internal Method		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Stress (Break)	435	psi	ISO 527-2		
Tensile Strain (Break)	680	%	ISO 527-2		
Hardness	Nominal Value	Unit	Test Method		
Shore Hardness (Shore A)	69		ISO 868		
Thermal	Nominal Value	Unit	Test Method		
Melting Temperature	156	°F	Internal Method		
Ring and Ball Softening Point	185	°F	ASTM E28		
Fill Analysis	Nominal Value	Unit	Test Method		
Brookfield Viscosity <sup>2</sup> (392°F)	5.50	Pa·s	Internal Method		

## Notes



<sup>&</sup>lt;sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>&</sup>lt;sup>2</sup> Spindle SC4-27