

# PRIMEVA® P33045

# **REPSOL - Ethylene Vinyl Acetate Copolymer**

Sunday, November 3, 2019

### **General Information**

#### **Product Description**

EVA resin REPSOL PRIMEVA® P33045 is recommended for hot melt adhesives applications, when toughness and flexibility are required. It contains antioxidant and free flowing agent.

#### Applications:

- · Hot Melt Adhesives
  - Packaging
  - · Bookbinding
  - · Pressure sensitive adhesive coatings

Recommended melt temperature below 200°C to avoid the decomposition of the polymer. Processing conditions should be optimised for each production line.

General			
Material Status	Commercial: Active		
Availability	<ul><li> Africa &amp; Middle East</li><li> Asia Pacific</li></ul>	<ul><li>Europe</li><li>Latin America</li></ul>	North America
Additive	Antioxidant	<ul> <li>Free Flowing Agent</li> </ul>	
Features	<ul><li>Antioxidant</li><li>Copolymer</li></ul>	<ul><li>Food Contact Acceptable</li><li>Good Flexibility</li></ul>	Good Toughness
Uses	<ul> <li>Adhesives</li> </ul>	<ul> <li>Packaging</li> </ul>	
Agency Ratings	EU Food Contact, Unspecified Rating		

ASTM & ISO Properties 1				
Physical	Nominal Value	Unit	Test Method	
Density (73°F)	0.956	g/cm³	ISO 1183	
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	45	g/10 min	ISO 1133	
Vinyl Acetate Content	33.0	wt%	Internal Method	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Stress (Break)	725	psi	ISO 527-2	
Tensile Strain (Break)	850	%	ISO 527-2	
Hardness	Nominal Value	Unit	Test Method	
Shore Hardness (Shore A)	73		ISO 868	
Thermal	Nominal Value	Unit	Test Method	
Melting Temperature	138	°F	Internal Method	
Ring and Ball Softening Point	234	°F	ASTM E28	
Fill Analysis	Nominal Value	Unit	Test Method	
Brookfield Viscosity <sup>2</sup>			Internal Method	
356°F	293	Pa·s		
392°F	169	Pa·s		

## Notes

<sup>&</sup>lt;sup>2</sup> Spindle SC4-27



<sup>&</sup>lt;sup>1</sup> Typical properties: these are not to be construed as specifications.