



Ravago Compounds HM-306 (Comp)

Ravago Manufacturing Americas - Medium Density Polyethylene

Tuesday, November 5, 2019

General Information

Product Description

Key Features:

- Excellent moldability
- Excellent long term outdoor weatherability (UV8)
- Balance of toughness and rigidity
- Excellent low temperature impact
- Excellent environmental stress crack resistance, ESCR
- Compounded for uniform additive dispersion
- Natural as well as standard, custom or special effect colors available
- Stock colors available. See Stock color bulletin
- Excellent opacity
- UL component recognition listing (E141240)
- Also available in powder form as HMP-306

General

Material Status	• Commercial: Active		
Availability	• North America		
Features	• Good Moldability • Good Stiffness	• Good Toughness • Good Weather Resistance	• High ESCR (Stress Crack Resist.) • Low Temperature Impact Resistance
Appearance	• Colors Available	• Opaque	
Forms	• Pellets		
Processing Method	• Compression Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.938		ASTM D792
Melt Mass-Flow Rate (190°C/2.16 kg)	5.0	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (ESCR) 100% Igepal, Compression Molded, F50	1000	hr	ASTM D1693B
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, Compression Molded)	2600	psi	ASTM D638
Tensile Elongation (Break, Compression Molded)	400	%	ASTM D638
Flexural Modulus - Tangent (Compression Molded)	120000	psi	ASTM D790
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 66 psi, Unannealed, Compression Molded	147	°F	ASTM D648
Deflection Temperature Under Load 264 psi, Unannealed, Compression Molded	106	°F	ASTM D648
Flammability	Nominal Value	Unit	Test Method
Flame Rating 0.06 in 0.12 in	HB HB		UL 94

Ravago Compounds HM-306 (Comp)

Ravago Manufacturing Americas - Medium Density Polyethylene

Notes

¹ Typical properties: these are not to be construed as specifications.