



TRIREX® Compound 3015NF

Samyang Corporation - Polycarbonate

Monday, November 4, 2019

General Information

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Features	• Flame Retardant		
Forms	• Pellets		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.20		ASTM D792
Melt Mass-Flow Rate (300°C/1.2 kg)	50	g/10 min	ASTM D1238
Molding Shrinkage - Flow	5.0E-3 to 7.0E-3	in/in	ASTM D955
Water Absorption (24 hr, 73°F)	0.15	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	7970	psi	ASTM D638
Tensile Elongation (Break)	100	%	ASTM D638
Flexural Modulus	327000	psi	ASTM D790
Flexural Strength (Yield)	11700	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	14	ft-lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	115		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 264 psi, Unannealed	189	°F	ASTM D648
CLTE - Flow	3.1E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	4.0E+16	ohms·cm	ASTM D257
Dielectric Strength	760	V/mil	ASTM D149
Dielectric Constant	2.90		ASTM D150
Dissipation Factor	9.0E-3		ASTM D150
Arc Resistance	90.0	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.020 in		V-0	
0.10 in	•	V-0	
	•	5VB	

Notes

¹ Typical properties: these are not to be construed as specifications.