



UNIVAL™ DMDA-6220 NT 7

The Dow Chemical Company - High Density Polyethylene Resin

Tuesday, November 5, 2019

General Information

Product Description

- Excellent stress crack resistance and rigidity
- High impact strength
- Moderate swell
- High melt strength

Complies with:

- U.S. FDA 21 CFR 177.1520 (c) 3.2a
- Canadian HPFB No Objection (with limitations)
- EU, No 10/2011

Consult the regulations for complete details.

UNIVAL™ DMDA-6220 NT 7 High Density Polyethylene (HDPE) Resin is an antistat containing, multipurpose polymer designed for the high speed production of blow molded containers used to package household industrial chemicals (e.g., detergents, bleach, fabric softeners), toiletries and cosmetics (e.g., shampoos, creams, lotions, etc.), health and medicinal aids, and food products. In addition, it can be blow molded into other thin walled parts and houseware items, and also can be extruded into profiles.

General

Material Status	• Commercial: Active		
Availability	• Latin America	• North America	
Additive	• Antiblock: No	• Processing Aid: No	• Slip: No
Agency Ratings	• EU No 10/2011	• FDA 21 CFR 177.1520(c) 3.2a	• HPFB (Canada) No Objection ¹
Forms	• Pellets		
Processing Method	• Blow Molding		

ASTM & ISO Properties²

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.955		ASTM D792
Melt Mass-Flow Rate			ASTM D1238
190°C/2.16 kg	0.38	g/10 min	
190°C/21.6 kg	33	g/10 min	
Environmental Stress-Cracking Resistance (ESCR)			ASTM D1693
122°F, 100% Igepal, F50	60.0	hr	
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	3900	psi	ASTM D638
Tensile Strength (Break)	4600	psi	ASTM D638
Tensile Elongation (Yield)	7.0	%	ASTM D638
Tensile Elongation (Break)	1000	%	ASTM D638
Flexural Modulus - 2% Secant	153000	psi	ASTM D790B
Impact	Nominal Value	Unit	Test Method
Tensile Impact Strength ³	80.0	ft-lb/in ²	ASTM D1822
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	62		ASTM D2240

UNIVAL™ DMDA-6220 NT 7

The Dow Chemical Company - High Density Polyethylene Resin

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	153	°F	ASTM D648
Brittleness Temperature	< -105	°F	ASTM D746
Vicat Softening Temperature	264	°F	ASTM D1525
Melting Temperature (DSC)	268	°F	Internal Method
Peak Crystallization Temperature (DSC)	246	°F	Internal Method

Additional Information

Plaque molded and tested in accordance with ASTM D4976.

Notes

¹ With limitations

² Typical properties: these are not to be construed as specifications.

³ Type S