



Ultradur® B 4300 G6

BASF Corporation - Polybutylene Terephthalate

Monday, November 4, 2019

General Information

Product Description

Ultradur B 4300 G6 is an easy flowing injection molding PBT with 30% glass fiber reinforcement for rigid, tough, and dimensionally stable parts.

Applications

Typical applications include windshield wiper arms, printed circuit boards, housings, consoles, contact carriers, and covers.

General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Features	• Good Dimensional Stability • Good Rigidity • Good Flow • Good Toughness
Uses	• Automotive Applications • Printed Circuit Boards • Housings • Protective Coverings
Agency Ratings	• EC 1907/2006 (REACH)
RoHS Compliance	• RoHS Compliant
Automotive Specifications	• CHRYSLER MS-DB-400 CPN2512 Color: 15043 Black • FORD WSK-M4D725-A Color: Natural • FORD ESB-M4D354-A1 • FORD WSS-M4D725-B1 • FORD WSK-M4D608-A • GM GMP.PBT.010 Color: Natural • FORD WSK-M4D725-A • GM QK 000488 Type A Color: Natural • GM QK 006615 R Color: Natural • IMDS ID 48049287 Color: Natural
Forms	• Pellets
Processing Method	• Injection Molding

ASTM & ISO Properties¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.53		ASTM D792
Density	1.53	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (250°C/2.16 kg)	11	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (0.125 in)	3.0E-3	in/in	
Molding Shrinkage			ISO 294-4
Across Flow	1.1	%	
Flow	0.34	%	
Water Absorption (Saturation)	0.40	%	ASTM D570
Water Absorption (Saturation, 73°F)	0.40	%	ISO 62
Water Absorption (Equilibrium, 50% RH)	0.20	%	ASTM D570
Water Absorption (Equilibrium, 73°F, 50% RH)	0.20	%	ISO 62
Viscosity Number (Reduced Viscosity)	102.0	ml/g	ISO 1628
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (73°F)	1.45E+6	psi	ISO 527-2
Tensile Strength (Break, 73°F)	19600	psi	ASTM D638
Tensile Stress			ISO 527-2
Break, -40°F	29600	psi	
Break, 73°F	19600	psi	

Ultradur® B 4300 G6

BASF Corporation - Polybutylene Terephthalate

Mechanical	Nominal Value	Unit	Test Method
Tensile Elongation (Break, 73°F)	2.5	%	ASTM D638
Tensile Strain			ISO 527-2
Break, -40°F	2.8	%	
Break, 73°F	2.5	%	
Tensile Creep Modulus (1000 hr)	1.09E+6	psi	ISO 899-1
Flexural Modulus (73°F)	1.17E+6	psi	ASTM D790
Flexural Modulus (73°F)	1.28E+6	psi	ISO 178
Flexural Stress (73°F)	29000	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	5.2	ft-lb/in ²	ISO 179
Charpy Unnotched Impact Strength			ISO 179
-22°F	35	ft-lb/in ²	
73°F	32	ft-lb/in ²	
Notched Izod Impact (73°F)	1.7	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	428	°F	ASTM D648
Heat Deflection Temperature (66 psi, Unannealed)	428	°F	ISO 75-2/B
Deflection Temperature Under Load			ASTM D648
264 psi, Unannealed	410	°F	
Heat Deflection Temperature (264 psi, Unannealed)	419	°F	ISO 75-2/A
Peak Melting Temperature	433	°F	ASTM D3418
Melting Temperature (DSC)	433	°F	ISO 3146
CLTE - Flow	1.4E-5	in/in/°F	
RTI Elec			UL 746
0.030 in	266	°F	
0.06 in	266	°F	
0.12 in	266	°F	
RTI Imp			UL 746
0.06 in	221	°F	
0.12 in	257	°F	
RTI Str (0.12 in)	284	°F	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity (0.0591 in)	1.0E+13	ohms	ASTM D257
Surface Resistivity	1.0E+13	ohms	IEC 60093
Volume Resistivity (0.0591 in)	> 1.0E+15	ohms·cm	ASTM D257
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Dielectric Constant			IEC 60250
100 Hz	4.00		
1 MHz	3.80		
Dissipation Factor			IEC 60250
100 Hz	2.5E-3		
1 MHz	0.017		
Comparative Tracking Index	375	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.06 in	HB		
0.12 in	HB		

Ultradur® B 4300 G6

BASF Corporation - Polybutylene Terephthalate

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	212 to 248	°F
Drying Time	4.0	hr
Suggested Max Moisture	0.040	%
Processing (Melt) Temp	482 to 518	°F
Mold Temperature	140 to 212	°F
Injection Pressure	508 to 1810	psi
Injection Rate	Fast	
Back Pressure	< 145	psi

Notes

¹ Typical properties: these are not to be construed as specifications.