

Ultradur® B 4560 BK10089

BASF Corporation - Polybutylene Terephthalate

Monday, November 4, 2019

General Information

Product Description

Ultradur B 4560 BK10089 is an injection molding, pigmented black, PBT grade.

Applications

Typical applications include industrial parts in the automotive field, such as head lamp bezels

General		
Material Status	Commercial: Active	
Availability	North America	
Uses	 Automotive Applications 	Industrial Parts
Agency Ratings	• EC 1907/2006 (REACH)	
RoHS Compliance	 RoHS Compliant 	
Automotive Specifications	• GM GMP.PBT.037	 GM GMP.PBT.037 Color: 10089 GM QK 006511 Color: 10089 Black
Appearance	Black	
Forms	• Pellets	
Processing Method	Injection Molding	

ASTM &	ASTM & ISO Properties 1					
Physical	Nominal Value	Unit	Test Method			
Density	1.30	g/cm³	ISO 1183			
Melt Volume-Flow Rate (MVR) (250°C/2.16 kg)	33	cm³/10min	ISO 1133			
Molding Shrinkage			ISO 294-4			
Across Flow	2.0	%				
Flow	1.5	%				
Viscosity Number (Reduced Viscosity)	112.0	ml/g	ISO 1628			
Mechanical	Nominal Value	Unit	Test Method			
Tensile Modulus (73°F)	377000	psi	ISO 527-2			
Tensile Stress (Yield, 73°F)	8700	psi	ISO 527-2			
Tensile Strain (Yield, 73°F)	4.0	%	ISO 527-2			
Nominal Tensile Strain at Break (73°F)	35	%	ISO 527-2			
Impact	Nominal Value	Unit	Test Method			
Charpy Notched Impact Strength (73°F)	1.7	ft·lb/in²	ISO 179			
Charpy Unnotched Impact Strength			ISO 179			
-22°F	40	ft·lb/in²				
73°F	67	ft·lb/in²				
Thermal	Nominal Value	Unit	Test Method			
Heat Deflection Temperature (66 psi, Unannealed)	275	°F	ISO 75-2/B			
Heat Deflection Temperature (264 psi, Unannealed)	140	°F	ISO 75-2/A			
Melting Temperature (DSC)	433	°F	ISO 3146			



Ultradur® B 4560 BK10089

BASF Corporation - Polybutylene Terephthalate

Processing Information				
Injection	Nominal Value	Unit		
Drying Temperature	212 to 248	°F		
Drying Time	4.0	hr		
Suggested Max Moisture	0.040	%		
Processing (Melt) Temp	482 to 518	°F		
Mold Temperature	104 to 176	°F		
Injection Pressure	508 to 1810	psi		
Injection Rate	Fast			
Back Pressure	< 145	psi		

Notes

¹ Typical properties: these are not to be construed as specifications.