



# Ultramid® A3L HP UV BK23220

BASF Corporation - Polyamide 66

Monday, November 4, 2019

## General Information

### Product Description

Ultramid A3L HP UV BK23220 is an unreinforced, impact modified, UV stabilized, high flow nylon 66 for injection molding. This grade has excellent flow and improved ambient and low temperature toughness.

### Applications

Typical applications include cable ties, fasteners and clamps.

### General

|                   |                                                                                                               |
|-------------------|---------------------------------------------------------------------------------------------------------------|
| Material Status   | • Commercial: Active                                                                                          |
| Availability      | • North America                                                                                               |
| Additive          | • Impact Modifier • UV Stabilizer                                                                             |
| Features          | • Good Toughness • Impact Modified • Oil Resistant<br>• High Flow • Low Temperature Toughness • UV Stabilized |
| Uses              | • Fasteners                                                                                                   |
| Agency Ratings    | • EC 1907/2006 (REACH)                                                                                        |
| RoHS Compliance   | • RoHS Compliant                                                                                              |
| Appearance        | • Black                                                                                                       |
| Forms             | • Pellets                                                                                                     |
| Processing Method | • Injection Molding                                                                                           |

## ASTM & ISO Properties <sup>1</sup>

| Physical                                          | Nominal Value | Unit                  | Test Method |
|---------------------------------------------------|---------------|-----------------------|-------------|
| Density                                           | 1.10          | g/cm <sup>3</sup>     | ISO 1183    |
| Mechanical                                        | Nominal Value | Unit                  | Test Method |
| Tensile Modulus (73°F)                            | 352000        | psi                   | ISO 527-2   |
| Tensile Stress (Yield, 73°F)                      | 8820          | psi                   | ISO 527-2   |
| Tensile Strain (Yield, 73°F)                      | 7.0           | %                     | ISO 527-2   |
| Nominal Tensile Strain at Break (73°F)            | 28            | %                     | ISO 527-2   |
| Flexural Modulus (73°F)                           | 323000        | psi                   | ISO 178     |
| Impact                                            | Nominal Value | Unit                  | Test Method |
| Charpy Notched Impact Strength                    |               |                       | ISO 179     |
| -22°F                                             | 4.1           | ft-lb/in <sup>2</sup> |             |
| 73°F                                              | 8.1           | ft-lb/in <sup>2</sup> |             |
| Notched Izod Impact Strength                      |               |                       | ISO 180     |
| -40°F                                             | 4.3           | ft-lb/in <sup>2</sup> |             |
| 73°F                                              | 8.6           | ft-lb/in <sup>2</sup> |             |
| Thermal                                           | Nominal Value | Unit                  | Test Method |
| Heat Deflection Temperature (66 psi, Unannealed)  | 378           | °F                    | ISO 75-2/B  |
| Heat Deflection Temperature (264 psi, Unannealed) | 158           | °F                    | ISO 75-2/A  |
| Melting Temperature (DSC)                         | 500           | °F                    | ISO 3146    |
| RTI Elec                                          |               |                       | UL 746      |
| 0.030 in                                          | 284           | °F                    |             |
| 0.12 in                                           | 284           | °F                    |             |

# Ultramid® A3L HP UV BK23220

## BASF Corporation - Polyamide 66

| Thermal      | Nominal Value | Unit | Test Method |
|--------------|---------------|------|-------------|
| RTI Imp      |               |      | UL 746      |
| 0.030 in     | 221           | °F   |             |
| 0.12 in      | 221           | °F   |             |
| RTI Str      |               |      | UL 746      |
| 0.030 in     | 230           | °F   |             |
| 0.12 in      | 230           | °F   |             |
| Flammability | Nominal Value | Unit | Test Method |
| Flame Rating |               |      | UL 94       |
| 0.030 in     | HB            |      |             |
| 0.12 in      | HB            |      |             |

### Processing Information

| Injection               | Nominal Value      | Unit |
|-------------------------|--------------------|------|
| Drying Temperature      | 140                | °F   |
| Drying Time             | 1.0 to 2.0         | hr   |
| Suggested Max Moisture  | 0.040 to 0.20      | %    |
| Processing (Melt) Temp  | 550 to 581         | °F   |
| Mold Temperature        | 140 to 212         | °F   |
| Injection Pressure      | 5080 to 18100      | psi  |
| Injection Rate          | Fast               |      |
| Back Pressure           | 0.00 to 50.8       | psi  |
| Screw Speed             | 40 to 80           | rpm  |
| Screw Compression Ratio | 3.0:1.0 to 4.0:1.0 |      |

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.